

<b>MINFILE Number:</b> 092GNW012	<b>Name:</b> WALLY	<b>Status:</b> Showing
----------------------------------	--------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
1 1989	N Assay/analysis Grab	Gold Silver Copper Molybdenum	3.9 g/t 101.8 g/t 3.28 % 2.62 %	sampling of the Wally 3 vein yielded values up to 3.9 grams per tonne gold, 101.8 grams per tonne silver, 3.28 per cent copper and 2.62 per cent molybdenum Assessment Report 18548
2 1989	N Assay/analysis Grab	Gold Silver Molybdenum Copper	0.51 g/t 18.8 g/t 0.058 % 1.62 %	three samples (900021-900023) of the Wally 3a vein yielded from 0.27 to 0.51 gram per tonne gold, 14.2 to 18.8 grams per tonne silver, 0.002 to 0.058 per cent molybdenum and 0.06 to 1.62 per cent copper Assessment Report 18548
2 1986	N Assay/analysis Grab	Gold	0.45 g/t	a grab (603701) sample from the Wally 3a vein Assessment Report 15577
1 1986	N Assay/analysis Chip	Gold	3.6 g/t	a chip sample (B039) of the Wally 3 vein yielded 3.6 grams per tonne gold over 0.65 metre Assessment Report 15577
1 1985	N Assay/analysis Grab	Gold Silver Copper	6.12 g/t 98.7 g/t 4.40 %	two grab samples of the vein yielded an average of 6.12 grams per tonne gold, 98.7 grams per tonne silver and 4.40 per cent copper (Samples 1 and 2) Assessment Report 14264.
1 1985	N Assay/analysis Drill Core	Molybdenum Copper Silver Gold	0.025 % 1 % 100 g/t 3.64 g/t	two drillcore samples, taken at approximately 8.69 and 9.45 metres down hole, yielded trace and greater than 0.025 per cent molybdenum, both greater than 1.00 per cent copper, greater than 100.0 and 37.0 grams per tonne silver with 1.91 and 3.64 grams per tonne gold, respectively Assessment Report 14264
1 1985	N Assay/analysis Drill Core	Gold Silver	1.1 g/t 3.8 g/t	hole DDH-17 on the vein zone yielded 1.1 grams per tonne gold and 3.8 grams per tonne silver over 1.5 metres Assessment Reports 14736 and 15577
1 1985	N Assay/analysis Drill Core	Gold	0.23 g/t	hole DDH-16 yielded 0.23 gram per tonne gold over 5.5 metres Assessment Reports 14736 and 15577
3 1984	N Assay/analysis Grab	Gold Silver Copper	0.30 g/t 4.2 g/t 0.10 %	a grab sample (BL 2 L500 25W) from the BL 2 L500 25W vein Assessment Report 12451