

MINFILE Number: 092GNW050	Name: NL	Status: Prospect
----------------------------------	-----------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
MAIN 2021	N Assay/analysis Rock	Gold	13.25 g/t	a rock sample (NL-1) of quartz vein material from the NL zone Assessment Report 39676
MAIN 2019	N Assay/analysis Rock	Gold	60.6 g/t	three closely spaced samples (DA19-S0009, -S0012 and -S0013) from the NL zone yielded values from 17.6 to 60.6 grams per tonne gold Assessment Report 39205
MAIN 2011	N Assay/analysis Chip	Gold Silver	9.0 g/t 21 g/t	a chip sample (87644) from the NL zone yielded 9.0 grams per tonne gold and 21 grams per tonne silver over 0.6 metre Assessment Report 32343
MAIN 2009	N Assay/analysis Grab	Gold Silver	161.01 g/t 228 g/t	a select grab sample (EG-09-03) from the centre of the NL vein yielded 161.01 grams per tonne gold and 228 grams per tonne silver, and a sample (EG-09-02) from the top 0.1 metre of the vein assayed 6.13 grams per tonne gold and 10 grams per tonne silver Assessment Report 31010
MAIN 1995	N Assay/analysis Rock	Gold Silver	2.81 g/t 4.46 g/t	a sample was taken from a shallow trench exposing the North Lake FW vein near Highway 101 where the vein splits into hangingwall and footwall portions separated by 61 centimetres of barren granodiorite. A grab sample (SWJR-1) from the footwall of the vein yielded 1.41 grams per tonne gold and 15.77 grams per tonne silver, and a grab sample (SWJR-2) of from the hangingwall of the vein yielded 2.81 grams per tonne gold and 4.46 grams per tonne silver Assessment Report 24069
MAIN 1995	N Assay/analysis Grab	Silver Gold	4.4600 g/t 2.8100 g/t	Grab sample SWJR-2, taken from the NL-HW (hangingwall) vein where the main vein splits near Highway 101. Assessment Report 24069.
MAIN 1993	N Assay/analysis Rock	Gold Silver	66.2 g/t 77.0 g/t	a sample (no. 6) from the NL vein Assessment Report 23354
MAIN 1988	N Assay/analysis Chip	Silver Gold	125.8 g/t 35.39 g/t	two samples (88 B-027 and 88 B-033) of mineralized quartz veins, 0.15 and 0.40 metre wide, from the NL zone yielded 125.8 and 35.7 grams per tonne silver with 35.39 and 22.05 grams per tonne gold Assessment Report 17941

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
1988	N	Assay/analysis Grab	Gold	6.85 g/t	a sample (WH-020) from several pieces of mineralized rubble at the TY zone Assessment Report 17941
			Silver	32.9 g/t	
1985	N	Assay/analysis Grab	Gold	6.99 g/t	grab samples from trenches on the TY zone yielded up to 6.99 grams per tonne gold and 175.5 grams per tonne silver Assessment Report 14736
			Silver	175.5 g/t	
1985	N	Assay/analysis Drill Core	Gold	2.78 g/t	a drillhole (TY-11) on the TY zone yielded 2.78 grams per tonne gold and 80 grams per tonne silver over 1.2 metres Assessment Report 14736
			Silver	80 g/t	
1985	N	Assay/analysis Drill Core	Gold	28.8 g/t	drilling on the NL vein yielded intercepts including 28.8 grams per tonne gold with 44.8 grams per tonne silver over 0.6 metre in hole NL DDH-3 Assessment Report 14736
			Silver	44.8 g/t	
1985	N	Assay/analysis Drill Core	Gold	37.0 g/t	over 0.9 metre in hole NL DDH-10 Assessment Report 14736
			Silver	27.5 g/t	
1985	N	Assay/analysis Drill Core	Gold	11.4 g/t	over 1.2 metres in hole NL DDH-12 Assessment Report 14736
			Silver	24.3 g/t	
1984	N	Assay/analysis Chip	Gold	7.5 g/t	a chip sample over 1.0 metre of intensely altered wallrock Assessment Report 12641
1982	N	Assay/analysis Chip	Gold	23.6 g/t	a chip sample of the main vein taken across a width of 0.46 metre Assessment Report 11129.
			Silver	40.1 g/t	
1982	N	Assay/analysis Chip	Silver	54.5000 g/t	samples of a tension vein taken over a length of 1.8 metres assayed 50.39 grams per tonne gold and 54.5 grams per tonne silver (Samples R-NL-1, R-NL-X-5) Assessment Report 11129.
			Gold	50.3900 g/t	