

MINFILE Number: 092GNW097	Name: TREAT	Status: Showing
----------------------------------	--------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
EAST 1993	Assay/analysis Chip	Silver	25.4 g/t	a chip sample (R10) taken from the area of the historical drillhole T1, several hundred metres east of the trenches, yielded 25.4 grams per tonne silver over 0.25 metre of pyritic andesite tuff hosting massive pyrite and minor sericite in fractures Assessment Report 23238
MAIN 1993	Assay/analysis Chip	Zinc Copper Silver	0.17 % 1.92 % 341.3 g/t	a chip sample (R7) from the area of trenching assayed 0.17 per cent zinc, 1.92 per cent copper and 341.3 grams per tonne silver over 0.80 metre of silicified andesite tuff hosting disseminated pyrite, chalcopyrite and sphalerite, whereas seven other nearby chip samples (R1 to R6 and R29) yielded values of 0.01 to 0.68 per cent zinc, trace to 0.22 per cent lead, 0.21 to 2.60 per cent copper with 33.0 to 182.6 grams per tonne silver over widths of 0.08 to 1.00 metre Assessment Report 23238.
NORTHEAST 1993	Assay/analysis Chip	Zinc	0.54 %	two 1.0-metre chip samples (R107 and R109) of silicified quartz monzonite and argillite hosting quartz stringers and pyrite, located approximately 600 metres east-northeast of the trenches, assayed 0.17 and 0.54 per cent zinc, respectively Assessment Report 23238
MAIN 1988	Assay/analysis Chip	Copper Zinc Silver	0.56 % 0.74 % 46.6 g/t	three chip samples (JRV88-R5 to -R7) from historical trenches exposing gossan and oxidized andesite hosting disseminated pyrite, chalcopyrite and pyrrothite yielded 0.56, 0.32 and 0.18 per cent copper, 0.74, 0.22 and 0.06 per cent zinc, with 46.6, 22.0 and 29.9 grams per tonne silver over 0.3, 4.0 and 1.0 metres, respectively Assessment Report 18346
DRILLHOLE 1971	Assay/analysis Drill Core	Copper	0.16 %	diamond drill hole T-2 is reported to have yielded 0.16 per cent copper over 3.1 metres Assessment Report 23238
DRILLHOLE 1971	Assay/analysis Drill Core	Copper	0.2 %	drillhole T-1, located several hundred metres to the east, is reported to have yielded 0.2 per cent copper over 9.1 metres Assessment Report 23238