

MINFILE Number:	092HNE002	Name:	MAL	Status:	Prospect
------------------------	-----------	--------------	-----	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2017	N	Assay/analysis Grab	Copper	1 %	a sample (J488628) of massive epidote with malachite staining assayed greater than 1.00 per cent copper and 0.396 gram per tonne gold Assessment Report 37096
			Gold	0.396 g/t	
2002	N	Assay/analysis Drill Core	Copper	0.79 %	diamond drilling yielded intercepts of 0.58, 0.47 and 0.79 per cent copper with 0.21, 0.21 and 0.14 gram per tonne gold over 0.76, 1.07 and 3.05 metres, respectively, in hole DM-1 Assessment Report 27039
			Gold	0.14 g/t	
2000	N	Assay/analysis Grab	Gold	0.097 g/t	a sample (11868) of epidote altered basalt with clots of pyrite-chalcopyrite and malachite staining from a historic trench Assessment Report 26469).
			Silver	22.3 g/t	
1981	N	Assay/analysis Drill Core	Copper	0.37 %	diamond drilling intercepted a series of massive pyrite lenses, up to 13 metres wide, in an andesitic volcanic breccia Assessment Report 9590
			Silver	6.8 g/t	
1980		Assay/analysis Grab	Silver	3.4000 g/t	Grab sample assay from the main trenched and drilled area. Assessment Report 8453.
			Gold	0.3400 g/t	
1980	N	Assay/analysis Grab	Copper	0.2000 %	
			Gold	0.34 g/t	
1965	Y	25,400 t Indicated	Copper	1.48 %	By 1965, drilling is reported to have identified a magnetite-chalcopyrite-pyrite lens striking north-northwest, dipping 60 degrees west, with a 36 metre strike length, a 54 metre dip length and a probably true width of 5.4 metres yielding an estimated indicated tonnage and grade for the plunging elliptical ore shoot of 25,400 tonnes grading 1.48 per cent copper with approximately 25 per cent magnetite Property File – 801029
			Magnetite	25 %	
1962		Assay/analysis Drill Core	Copper	1.6200 %	Best result from early diamond drilling, over 6 metres. Assessment Report 449.