

| | | | | | |
|------------------------|-----------|--------------|-----------------------|----------------|----------|
| MINFILE Number: | 092HNE006 | Name: | INDEPENDENCE (L.1696) | Status: | Prospect |
|------------------------|-----------|--------------|-----------------------|----------------|----------|

| Ore Zone/ Year/Report On | | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|---|------------------------------|------------|----------|---|
| 2016 | N | Assay/analysis Chip | Copper | 0.47 % | rock chip samples from outcrop near the historic workings of the Independence occurrence (Sample Q980327) Assessment Report 36939 |
| | | | Molybdenum | 0.016 % | |
| 1997 | N | Assay/analysis Chip | Copper | 0.154 % | chip sampling of trenches on the Homestead zone yielded 0.154 and 0.100 per cent copper over 6 and 18 metres in trenches 97-4 and 97-5, respectively Assessment Report 25293 |
| | | | | | |
| 1997 | N | Assay/analysis Drill Core | Copper | 0.107 % | drilling on the Homestead zone yielded 0.123 and 0.107 per cent copper over 7.62 and 45.72 metres in holes 580-RC1 and 580-RC2, respectively Assessment Report 25293 |
| | | | | | |
| 1988 | N | Assay/analysis Drill Core | Copper | 0.64 % | percussion drilling, located near the old workings, is reported to have yielded up to 0.64 per cent copper over 6.1 metres in hole PDH-88-B Assessment Report 24984 |
| | | | | | |
| 1987 | | Assay/analysis Chip | Copper | 0.6091 % | Across 9 metres of silicified and carbonate-altered breccia with pyrite, chalcopyrite, malachite and azurite. Assessment Report 17431, page 8. |
| | | | | | |
| 1972 | N | Assay/analysis Chip | Copper | 1.12 % | two 6 metre chip samples from areas of stripping are reported to have yielded 1.12 and 0.94 per cent copper, respectively Assessment Report 17431 |
| | | | | | |
| 1965 | N | Assay/analysis Drill Core | Copper | 0.13 % | a drill hole (No.1), located approximately 2.1 kilometres south east of the Independence workings, over 15 metres, near the end of the hole. Assessment report 707 |
| | | | | | |
| 1965 | N | Assay/analysis Drill Core | Copper | 0.1190 % | Average grade over 149 metres in hole no. 4 (2.4-151.5 metres down-hole), including 57.9 metres grading 0.125 per cent copper and 0.020 per cent molybdenum (93.6 to 151.5 metres down-hole) Assessment Report 707 |
| | | | Molybdenum | 0.0110 % | |
| 1965 | N | Assay/analysis Drill Core | Copper | 0.135 % | hole no 2, located 1530 metres north of the previous hole, intersected 0.135 per cent copper and 0.0056 per cent molybdenum over 45.7 metres (9.1 to 54.9 metres) Assessment Report 707 |
| | | | Molybdenum | 0.0056 % | |
| 1958 | N | Assay/analysis Drill Core | Copper | 4.84 % | drilling near the main adit is reported to have yielded up to 4.84 per cent copper over 3.3 metres and 0.80 per cent copper over 12.0 metres Assessment Report 17431 |
| | | | | | |

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|----------------------|-----------|-------|------------------------|
|-----------------------------|----------------------|-----------|-------|------------------------|