

MINFILE Number:		Name:		Status:	
Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments	
SOUTHEAST 2017	N	Gold Assay/analysis Grab	0.425 g/t	an outcrop sample (J488626) of gabbro(?) with carbonate-specular hematite-pyrite veinlets, located approximately 550 metres south- southeast of the lower adit Assessment Report 37096	
TRENCH 2017	N	Copper Assay/analysis Grab	0.773 %	a float sample (J488625) of altered and brecciated gabbro hosting clots of chalcopyrite from a historic trench, located several hundred metres northwest of the lower adit Assessment Report 37096	
DRILLHOLE 2010	N	Copper Gold Assay/analysis Drill Core	1.06 % 0.317 g/t	over 15.69 metres of highly altered, brecciated and silicified andesite flow, including 1.76 per cent copper over 9.15 metres and 4.317 grams per tonne gold over 0.46 metre in hole 10-5 on the South zone and 1.85 per cent copper over 1.2 metres in hole 10-4 on the Main (Lower Adit) zone Assessment Report 32160	
DRILLHOLE 2008	N	Gold Copper Assay/analysis Drill Core	8.6 g/t 0.24 %	a drill hole (VRW08-02) on the Adit vein yielded up to 8.6 grams per tonne gold and 0.24 per cent copper over 1 metre of the hanging wall section of the vein, while the footwall of the vein yielded 1.1 grams per tonne gold and 0.09 per cent copper over 1.0 metre. Other drill holes testing the vein along strike and at depth yielded up to 4.6 grams per tonne gold over 0.75 metres in hole VRW08-05, 1.32 grams per tonne gold over 2.77 metres in hole VRW08-04 and 0.14 gram per tonne gold with greater than 1.00 per cent copper over 1.26 metres in hole VRW08-03. Drill core recovery was reported to be poor due to a high degree of pyrite. Assessment Report 30728	
TRENCH 2000	N	Gold Copper Assay/analysis Grab	0.616 g/t 0.145 %	a grab sample (11854) from a historic trench, located to the northwest of the lower adit Assessment Report 26469	
TRENCH 1996	N	Gold Assay/analysis Grab	34 g/t	grab samples from a historic trench (G) on the Upper zone yielded greater than 34 grams per tonne gold Assessment Report 24800	

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
DRILLHOLE 1996	N Assay/analysis Drill Core	Gold Silver Copper	16.58 g/t 12.9 g/t 0.75 %	diamond drilling on the Main Vein yielded 16.58 grams per tonne gold, 12.9 grams per tonne silver and 0.75 per cent copper over 6.57 metres (62.18 to 68.73 metres down-hole) in hole W96-1, 0.13 per cent copper and 1.78 grams per tonne gold over 5.18 metres in hole W96-10 and 3.95 grams per tonne gold, 9.86 grams per tonne silver and 1.12 per cent copper over 2.36 metres in hole W96-16 Assessment Report 24800
DRILLHOLE 1996	N Assay/analysis Drill Core	Gold	27.7 g/t	drilling of the Stockwork zone yielded 2.11 per cent copper, 20.1 grams per tonne silver and 2.61 grams per tonne gold over 3.35 metres in hole W96-3 and 27.7 grams per tonne gold over 0.53 metre in hole W96-15 Assessment Report 24800
DRILLHOLE 1996	N Assay/analysis Drill Core	Copper Silver	1.12 % 13.0 g/t	over 0.76 metre in hole W96-13 of the Upper zone Assessment Report 24800
ADIT 1972	N Assay/analysis Chip	Copper Silver Gold	6.05 % 10.3 g/t 0.7 g/t	a chip sample from the No. 1 adit over 6 metres Assessment Report 4230.
DRILLHOLE 1972	N Assay/analysis Drill Core	Silver Copper	3.4000 g/t 1.1200 %	drilling yielded intersections of up to 0.08 per cent copper over 86.9 metres, including 1.12 per cent copper and 3.4 grams per tonne silver over 1.5 metres (81.0 to 82.5 metres down-hole) and 0.84 per cent copper with 6.8 grams per tonne silver over 3.0 metres (34.1 to 37.1 metres down-hole) in hole HNS 72-1 on the main zone Assessment Report 4230.
DUMP 1972	N Assay/analysis Grab	Copper Silver Gold	4.84 % 46.5 g/t 0.7 g/t	A grab sample from the dump of the No. 3 adit Assessment Report 4230
TRENCH 1972	N Assay/analysis Chip	Copper Silver Gold	1.72 % 37.6 g/t 0.7 g/t	chip samples from 6E trench over 4.5 metres Assessment Report 4230
TRENCH 1966	N Assay/analysis Chip	Copper Silver	1.30 % 23.9 g/t	sampling of trench no. 3 over 1.2 metres Property File 801604
ADIT 1966	N Assay/analysis Chip	Copper Silver	1.5 % 14.2 g/t	ampling of the adit yielded a weighted average of 1.5 per cent copper and 14.2 grams per tonne silver over 5.7 metres Property File 801604