

MINFILE Number:		Name:		Status:	
Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments	
ADIT 1990	N	Copper Assay/analysis Chip	0.503 % 3.0 g/t	Chip samples (27689 and 27688) from an adit (No. 19) and a nearby pit yielded 0.503 and 0.328 per cent copper over 2 and 4 metres, respectively. Property File - 861119	
SHAFT 1990	N	Copper Silver Assay/analysis Chip	0.855 % 3.0 g/t	Three chip samples (27684 through 27686) taken from three separate shafts (No. 21, 20 and 22), separated over a strike length of approximately 70 metres, yielded from 0.485 to 0.855 per cent copper and 1.4 to 3.0 grams per tonne silver over 1.0 to 1.2 metre widths. Property File - 861119	
SAMPLE 1913	N	Copper Gold Silver Assay/analysis Chip	0.9 % 0.7 g/t 10 g/t	Over 4.6 metres. Minister of Mines Annual Report 1901, page 1180	
TRENCH 1901		Silver Gold Copper Assay/analysis Chip	10.0000 g/t 0.7000 g/t 0.9000 %	Chip sample taken across 4.6 metres. Minister of Mines Annual Report 1901, page 1180.	