

<b>MINFILE Number:</b>	092HNE074	<b>Name:</b>	BIG KIDD	<b>Status:</b>	Prospect
------------------------	-----------	--------------	----------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2012	N	Assay/analysis	Copper	0.11 %	Drilling yielded intercepts of 0.32 gram per tonne gold and 0.11 per cent copper over 156.0 metres (6.0 to 162.0 metres down-hole), 1.15 grams per tonne gold and 0.19 per cent copper over 16 metres (283.0 to 299.0 metres down-hole), 0.53 gram per tonne gold and 0.37 per cent copper over 18 metres (362.0 to 380.0 metres down-hole) and 0.99 gram per tonne gold with 0.08 per cent copper over 20 metres (501.0 to 530.0 metres down-hole) in hole BK-19-002; 0.34 gram per tonne gold and 0.10 per cent copper over 112.0 metres (187.0 to 299.0 metres down-hole) in hole BK-19-004; 0.31 gram per tonne gold and 0.11 per cent copper over 204.0 metres (97.0 to 291.0 metres down-hole) in hole BK-19-005; 0.30 gram per tonne gold and 0.13 per cent copper over 161.5 metres (65.0 to 226.5 metres down-hole) in hole BK-19-008 and 0.21 gram per tonne gold with 0.13 per cent copper over 214.5 metres (192.0 to 406.5 metres down-hole) in hole BK-19-009. Assessment Report 38825
		Drill Core	Gold	0.32 g/t	
2003	N	Assay/analysis	Gold	0.51 g/t	Over 56 metres in hole DDH0305. Folk, P.G. (2011-05-12): Technical Report on the Big Kidd Property
		Drill Core	Copper	0.10 %	
1999	N	Assay/analysis	Gold	0.62 g/t	Over 70.3 metres. Folk, P.G. (2011-05-12): Technical Report on the Big Kidd Property
		Drill Core	Copper	0.20 %	
1997	N	Assay/analysis	Copper	0.124 %	Drill hole BK97-05, located near the 1992 hole 92-1, yielded a 115.96 metre intersection graded 0.801 grams per tonne gold and 0.124 per cent copper, including a higher grade section of 19.46 metres grading 3.09 grams per tonne gold and 0.113 per cent copper, while hole BK97-04 extended the mineralized zone over 40 metre laterally yielding 0.93 gram per tonne gold and 0.18 per cent copper over 59.56 metres. Assessment Report 25611; Exploration in B.C. 1997, page 38
		Drill Core	Gold	0.801 g/t	
1992	N	Assay/analysis	Copper	0.2 %	Drilling yielded intercepts of up to 0.75 gram per tonne gold and 0.2 per cent copper over the final 71 metres of hole 91-1 located in the north zone of the Big Kidd breccia. Assessment Report 26138
		Drill Core	Gold	0.75 g/t	

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
TRENCH			Gold	0.56 g/t	Sampling of trench 92-2 is reported to have yielded 0.56 gram per tonne gold and 0.112 per cent copper over 32.5 metres. Assessment Report 26138
1992	N	Assay/analysis Chip	Copper	0.112 %	
ADIT			Copper	1.357 %	A select grab sample (114214) from the adit/shaft area Assessment Report 21824
1991	N	Assay/analysis Grab	Gold	0.320 g/t	
TRENCH			Copper	0.115 %	Trenching and sampling of the northern margin of the breccia pipe exposed in trench 80-4, located northwest of the no. 1 adit, yielded 0.115 per cent copper and 1.23 grams per tonne gold over 12 metres, including 0.121 per cent copper and 1.97 grams per tonne gold over 6 metres. Assessment Report 8743
1980	N	Assay/analysis Chip	Gold	1.23 g/t	
TRENCH			Copper	0.237 %	Channel sampling of trench no. 12, located approximately 140 metres west of adit no 1, yielded 0.237 per cent copper, 0.095 gram per tonne gold and 3.37 gram per tonne silver over 35 metres (50 to 85 metres along the trench), while five grab samples from 100 to 180 metres along the trench yielded an average of 0.221 per cent copper with 3.16 grams per tonne silver and a further channel sample (taken from 185 to 190 metres along the trench) yielded 0.618 per cent copper with 5.0 grams per tonne silver. Assessment Report 7100
1978	N	Assay/analysis Chip	Silver	3.37 g/t	
			Gold	0.095 g/t	
			Copper	0.237 %	
ADIT			Silver	13.6600 g/t	Average grade over 14 metres. Assessment Report 7100, page 8.
1978	N	Assay/analysis Channel	Gold	0.1410 g/t	
			Copper	0.9010 %	
DRILLHOLE			Copper	0.14 %	Drill holes 72-6 and 72-7, located on the occurrence area, yielded 0.16 and 0.14 per cent copper over 12.0 and 22.5 metres, respectively, while another drill hole (72-12), located several hundred metres to the north yielded an average of 0.14 per cent copper over 90 metres. Property File – 681185
1972	N	Assay/analysis Drill Core			
SAMPLE			Copper	1.45 %	Samples from a volcanic breccia zone with chalcopyrite mineralization on the Dote 10 claim is reported to have yielded from 0.35 to 1.45 per cent copper with 11.3 grams per tonne silver over 15 metres. Property File – 8531 and 8532
1966	N	Assay/analysis Chip	Silver	11.3 g/t	
DRILLHOLE			Copper	0.28 %	Over 36.3 metres (103.2 to 139.5 metres down-hole) in hole No. 2. Property File - 861157
1965	N	Assay/analysis Drill Core			