

MINFILE Number:		Name:		Status:	
Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments	
DUMP 1997	N	Assay/analysis Grab	Copper Silver Gold	5.32 % 191.6 g/t 0.275 g/t	A grab sample (125855) from the shaft dump. Assessment Report 25611
OUTCROP 1997	N	Assay/analysis Chip	Copper Silver Gold	0.671 % 9.4 g/t 0.085 g/t	Two outcrop panel samples (125853 and 125854) from the shaft area yielded 0.671 and 0.290 per cent copper, 9.4 and 5.4 grams per tonne silver with 0.085 and 0.020 gram per tonne gold over 0.6 and 0.5 metre, respectively. Assessment Report 25611
RIDGE 1997	N	Assay/analysis Grab	Copper Silver	4.55 % 20.8 g/t	A grab sample (125851) over a 1 metre outcrop of volcanics hosting stockworks of fine-grained chalcocite veins, up to 2 centimetres wide, located on the ridge approximately 250 metres west of the shaft. Assessment Report 25611
DRILLHOLE 1973	N	Assay/analysis Drill Core	Copper	1.09 %	Over 38.4 metres in hole no. 1, while a second hole (No. 2), located 90 metres west of the first hole is reported to have yielded approximately 1 per cent copper over 18 metres. Property File - 823662
SHOWING 1928		Assay/analysis Grab	Silver Gold Copper	206.0000 g/t 0.7000 g/t 8.8000 %	Minister of Mines Annual Report 1928, page 223.