

| | | |
|----------------------------------|---------------------------------------|------------------------|
| MINFILE Number: 092HNE083 | Name: BANK OF ENGLAND (L.1130) | Status: Showing |
|----------------------------------|---------------------------------------|------------------------|

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|-----------------------------|-----------|----------|--|
| SHOWING | | Copper | 0.4800 % | Sample taken over 35 metres. |
| 1992 | N Assay/analysis Chip | | | George Cross News Letter No. 90 (May 8), 1992. |
| TRENCHES | | Copper | 3.30 % | Two grab samples (ASG90103 and ASG90104) of malachite bearing diorite or diorite breccia and dioritic lahar from historic pits or trenches yielded 3.30 and 3.00 per cent copper with 17.3 and 3.8 grams per tonne silver, respectively. |
| 1990 | N Assay/analysis Grab | | | Assessment Report 20551 |
| OPENCUT | | Copper | 1.5 % | A sample from the face of an opencut. |
| 1901 | N Assay/analysis Rock | Gold | 1.4 g/t | Minister of Mines Annual Report 1901, page 1182 |