

MINFILE Number:	092HNE084	Name:	PAYCINCI	Status:	Developed Prospect
------------------------	-----------	--------------	----------	----------------	--------------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
PAYCINCI		1,800 kt	Copper	1.0000 %	Reserve estimate. Tom Schroeter, 1998.
1998	Y	Inferred			
PIT			Copper	2.38 %	A sample (618-K) from the shaft or pit exposing a 2-metre wide shear zone with malachite staining. Assessment Report 24019
1995	N	Assay/analysis Grab			
TRENCHES			Copper	2.99 %	Chip sampling (618-I, -J, -L, -M and -N) of trenches located near an infilled shaft or test pit yielded from 0.76 per cent copper over 15 metres to 2.99 per cent copper over 4 metres. Assessment Report 24019
1995	N	Assay/analysis Chip			
TRENCHES			Copper	1.25 %	Chip sampling of the Cincinatti and Sherwin trenches, located approximately 100 and 300 metres to the south of the adit, respectively, yielded 1.25 and 0.29 per cent copper over 10 and 25 metres, respectively. Assessment Report 22382
1992	N	Assay/analysis Chip			
ADIT			Copper	0.198 %	Sample (92022) from the Cincinnatti adit area. Assessment Report 22382
1992	N	Assay/analysis Rock			
TRENCHES			Copper Silver	2.4 % 5.7 g/t	Six rock samples (2051 to 2056) from historic trenches, extending for approximately 500 metres along a north-south strike, analysed 1.1 to 2.4 per cent copper, 0.005 to 0.010 gram per tonne gold and 1.3 to 5.7 grams per tonne silver. Assessment Report 14108, Figure 5
1985	N	Assay/analysis Rock			
CINCINNATTI		54 kt	Copper	0.8760 %	Drill indicated reserves based on 2 drillholes. Assessment Report 7654.
1979	Y	Indicated			