

<b>MINFILE Number:</b>	092HNE092	<b>Name:</b>	SHAMROCK	<b>Status:</b>	Prospect
------------------------	-----------	--------------	----------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2017	N	Assay/analysis Rock	Copper	6.43 %	Two samples (Aspen-2 and -3) from the Shear zone and Extension adits yielded 6.43 and 3.18 per cent copper with 8.4 and 4.9 grams per tonne silver, respectively. Assessment Report 37347
			Silver	8.4 g/t	
1985	N	Assay/analysis Rock	Copper	7.495 %	three samples (2151R, 2299 and 3000) from an area of trenches yielded values from 3.388 to 7.495 per cent copper, 0.006 to 0.019 per cent molybdenum and 1.4 to 52.4 grams per tonne silver. Assessment Report 14141
			Silver	52.4 g/t	
1973		Assay/analysis Chip	Copper	1.4200 %	Average grade of sampling over a length of 30 metres and an average width of 5.2 metres. National Mineral Inventory.
1972	N	Assay/analysis Chip	Copper	2.40 %	Average of three chip samples, taken across widths of 4.3 to 4.9 metres and spaced evenly over a strike length of 17 metres from the main shear zone. Assessment Report 3955
			Silver	4.8 g/t	
			Gold	0.10 g/t	
1972	N	Assay/analysis Grab	Copper	0.23 %	A series of grab samples, taken over 60 metres, from the southwestern trenched area. Assessment Report 3955
1969	N	Assay/analysis Chip	Copper	1.42 %	Sampling of trenches is reported to have yielded an average of 1.42 per cent copper over a width of 5.1 metres and a length of 30 metres. Property File – 8537