

## MINFILE Inventory Detail Report BC Geological Survey Ministry of Energy, Mines and Petroleum Resources

MINFILE Number:	092HNE099	Name: RUM	1	Status: Prospect
Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2018 N	Assay/analysis Rock	Copper Gold	0.336 % 0.203 g/t	A rock sample (662346) of malachite stained and clay altered hornblende microdiorite from the occurrence area.  Assessment Report 37685
SAMPLE 2015 N	Assay/analysis Rock	Copper Silver Gold	0.624 % 4.1 g/t 0.608 g/t	A rock sample from the occurrence area Assessment Report 36184
SAMPLE 2010 N	Assay/analysis Grab	Copper Gold	0.698 % 0.672 g/t	a grab sample (55109) taken over 5 metres of sericite altered crystal stuff sub-crop rubble Assessment Report 31916
TRENCH 2009 N	Assay/analysis Chip	Copper Gold	1 % 0.362 g/t	A chip sample from a historic trench yielded greater than 1.00 per cent copper and 0.362 gram per tonne gold.  Assessment Report 31138
PIT 2009 N	Assay/analysis Grab	Copper Gold	0.388 % 0.361 g/t	A grab sample (S-01) from a historic pit exposing malachite-stained altered andesite, located approximately 500 metres north of the trenches.  Assessment Report 31138
OUTCROP 2000 N	Assay/analysis Grab	Copper	0.123 %	An outcrop grab sample (KHS1005) of fine-grained intrusive with pyrite and chalcopyrite. Assessment Report 26421
TRENCHES  1994 N	Assay/analysis Rock	Copper Gold	0.767 % 0.075 g/t	Samples from historic trenches Assessment Report 23775
SAMPLE 1985 N	Assay/analysis Chip	Gold	0.071 g/t	Sample R1 over 15 metres of fractured and altered microdiorite. Assessment Report 14304
DRILLHOLE 1975 N	Assay/analysis Drill Core	Copper	0.09 %	Percussion hole PR 10 over 27.4 metres (9.2 to 36.6 metres down-hole).  Property File - L. Sookochoff, 1975, pages 10-11
DRILLHOLE 1975 N	Assay/analysis Drill Core	Copper	1.41 %	Core from a diamond-drill hole (K-3) over 0.76 metre (48.62 to 49.38 metres down-hole).  Property File - L. Sookochoff, 1975, pages 10-11

Ore Zor Year/Repo		Tonnage/ Category	Commodity	Grade	Reference/ Comments
TRENCH		Assay/analysis	Copper	0.1600 %	Average grade over 183 metres, including 0.29 per cent over 53.3 metres.
1975	N	Chip			Property File - Sookochoff, L., 1975, page 9 (trench 7).
TRENCH			Copper	0.10 %	Trench 8W over 137 metres
		Assay/analysis			Assessment Report 6036; Property File - L.
1975	N	Chip			Sookochoff, 1975

Monday, July 7, 2025 MINFILE Number: 092HNE099 Page 2 of 2