

MINFILE Number:	092HNE143	Name:	AXE (ADIT ZONE)	Status:	Developed Prospect
------------------------	-----------	--------------	-----------------	----------------	--------------------

Ore Zone/ Year/Report On		Tonnage/ Category		Commodity	Grade	Reference/ Comments
ADIT				Copper	0.203 %	A drillhole (AXD18-04) on the Adit zone yielded intercepts including 0.233 and 0.203 per cent copper with 0.136 and 0.027 gram per tonne gold over 28.0 and 63.0 metres (196.0 to 224.0 and 270.0 to 333.0 metres down-hole), respectively Assessment Report 38199
2018	N	Assay/analysis	Drill Core	Gold	0.027 g/t	
NORTHWEST				Copper	0.704 %	A grab sample (Y096039) of propylitic altered diorite, located approximately 330 metres north-northwest of the Adit zone. Assessment Report 38199
2018	N	Assay/analysis	Grab	Gold	0.094 g/t	
ADIT				Copper	0.3 %	Two holes have intersections of oxide-only mineralization. The oxide zones are 13.5 and 43.5 metres in length, with grades of 0.10 and 0.13 per cent oxide copper, respectively. Two holes have intersections of oxide and possibly supergene sulphide copper mineralization. These zones are 33.0 and 10.5 m in length, with grades of 0.19 and 0.11 per cent sulphide copper and 0.12 and 0.22 per cent oxide copper, respectively. The total copper grade is approximately 0.3 per cent copper. All holes encountered primary copper sulphide mineralization. The intersections are 15.0, 3.6 and 23.6 metres in length, with grades of 0.17, 0.15 and 0.52 per cent copper, respectively. Later in 2004, a reverse circulation program was completed on the property and yielded intercepts of up to 0.32 per cent copper over 71.7 metres (4.0 to 75.6 metres down-hole) in hole 04-005 Assessment Report 27891
2004	N	Assay/analysis	Drill Core			
ADIT		6,100	kt	Copper	0.59 %	The resource was based on a 0.25 per cent copper cut-off grade. The gold content has not been determined. Assessment Report 29096
2003	N	Indicated				
ADIT		6,100	kt	Copper	0.59 %	The resource was based on a 0.25 per cent copper cut-off grade. The gold content has not been determined. Assessment Report 29096
2003	N	Inferred				
MIDDLE D		300	kt	Copper	0.55 %	Mid zone, the resource was based on a 0.25 per cent copper cut-off grade. The gold content has not been determined. Assessment Report 29096
2003	N	Indicated				
MIDDLE D		300	kt	Copper	0.55 %	The resource was based on a 0.25 per cent copper cut-off grade. The gold content has not been determined. Assessment Report 29096
2003	N	Inferred				

Ore Zone/ Year/Report On		Tonnage/ Category		Commodity	Grade	Reference/ Comments
TOTAL		39,100	kt	Copper	0.39 %	At a 0.25 per cent copper cut-off. The original year and source of the resource estimate is not known. This total resource includes other Axe zones 092HNE040 and 092HNE142. Exploration and Mining in BC 2003, page 55
2003	N	Indicated				
TOTAL		32,000	kt	Copper	0.39 %	The inferred resource is reported to be of similar grade to the indicated resource. This total inferred resource includes other Axe zones (092HNE040 and 142). Exploration and Mining in BC 2003, page 55.
2003	N	Inferred				
NORTH				Gold	0.798 g/t	A rock sample (AR-08) over 1.6 metres, taken approximately 500 metres north of the Adit zone. Assessment Report 25761
1994	N	Assay/analysis	Rock			
ADIT				Copper	2.4 %	A select grab sample (ADIT-R7) from the Adit zone yielded 2.4 per cent copper and 4.3 grams per tonne silver over 1.5 metres Assessment Report 25761
1994	N	Assay/analysis	Chip	Silver	4.3 g/t	
ADIT				Copper	0.408 %	a drill hole (82-3), located east of the 1973 drillholes, yielded intercepts of 0.065 per cent copper, 0.492 per cent zinc, 11.3 grams per tonne silver and 0.123 gram per tonne gold over 15.0 metres (30.0 to 45.0 metres down-hole), including 0.0677 per cent copper, 0.420 gram per tonne gold, 35.2 grams per tonne silver and 1.038 per cent zinc over 3.05 metres; 0.408 per cent copper with 2.6 grams per tonne silver over 22.0 metres (60.0 to 82.2 metres down-hole), including greater than 2.980 per cent copper and 17.0 grams per tonne silver over 0.6 metre and 0.764 per cent copper with 4.4 grams per tonne silver over 15.9 metres (95.4 to 111.3 metres down-hole), Assessment Report 10886
1982	N	Assay/analysis	Drill Core	Silver	2.6 g/t	
ADIT				Copper	2.97 %	Three rock samples (AD-1 through -3) from the Adit zone yielded from 1.64 to 2.97 per cent copper and 2.6 to 7.4 grams per tonne silver. Assessment Report 9896
1981	N	Assay/analysis	Rock	Silver	7.4 g/t	
ADIT		14,513,600	t	Copper	0.5600 %	Northern Miner - September 6, 1973.
1973	Y	Indicated				