

MINFILE Inventory Detail Report BC Geological Survey Ministry of Energy, Mines and Petroleum Resources

MINFILE Number:		092HNE144	Name: AU-WEN		Status: Prospect	
Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments	
H 2000	N	Assay/analysis Rock	Gold	0.716 g/t	a sample from the Hodge vein yielded 0.716 gram per tonne gold. Assessment Report 26469	
MAIN 2000	N	Assay/analysis Rock	Gold Copper	0.260 g/t 0.403 %	Sampling of the Nesbitt zone yielded values from 0.085 to 0.260 gram per tonne gold with up to 0.403 per cent copper. Assessment Report 26469	
MAIN 1996	N	Assay/analysis Chip	Gold	1.032 g/t	Sampling of a trench on the Nesbitt zone yielded an average 1.032 grams per tonne gold over 8.5 metres, including narrow (2-centimetre wide) zones of higher-grade material yielding up to 43.8 grams per tonne gold. Assessment Report 24806	
H 1996	N	Assay/analysis Chip	Gold Silver Copper	116.3 g/t 75.2 g/t 0.14 %	Sampling of trenches on the Hodge zone yielded from 10.8 to 116.3 grams per tonne gold with an average of 57.1 grams per tonne gold over 0.1 metre and up to 75.2 grams per tonne silver and 0.14 per cent copper. Also at this time, a 1.3 metre wide section of vein and shattered wall rock yielded 14.7 grams per tonne gold. Assessment Report 24806	
MAIN 1983	N	Assay/analysis Chip	Gold	10.8000 g/t	Previous sampling on the Nesbitt (Main) zone was reported to have yielded significant gold assays in chip samples range from 6.8 grams per tonne over 5.1 metres to 10.8 grams per tonne over 4.9 metres. The year(s) of sampling is unknown. Assessment Report 16008.	
MAIN 1979	N	Assay/analysis Chip	Gold	14.60 g/t	Sampling of trenches on the Nesbitt zone yielded 14.60 grams per tonne gold over 1.47 metres in trench 2 and 9.8 grams per tonne gold over 1.53 metres in trench 3. Assessment Report 7293	
MAIN 1975	N	Assay/analysis Grab	Gold	91.0000 g/t	Grab samples (no. 2) over 2.1 metres of the Nesbitt (Main) zone yielded 21.2 grams per tonne gold, while select samples (Nos. 3 and 4) over a 1.2 by 15 and 2.1 by 18 metre areas yielded 91.0 and 78.7 grams per tonne gold, respectively. Assessment Reports 5766, 16008.	

Saturday, October 25, 2025 MINFILE Number: 092HNE144 Page 1 of 1