

<b>MINFILE Number:</b> 092HNE167	<b>Name:</b> BLUEY	<b>Status:</b> Showing
----------------------------------	--------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2006	N Chip	Assay/analysis Copper Lead Zinc Silver	0.919 % 0.155 % 0.797 % 10.9 g/t	A chip sample (K-04) over 4 metres. Assessment Report 28782
SAMPLE 1997	N Grab	Assay/analysis Copper Lead Zinc Cadmium Silver	1.035 % 0.353 % 3.926 % 0.053 % 9.9 g/t	Three grab samples (28331 through 28333) of porphyritic basalt with fracture related pyrite, azurite, malachite and epidote, located in the approximate vicinity of this mineralized zone, yielded from 0.261 to 1.035 per cent copper, 0.133 to 0.353 per cent lead, 0.140 to 3.926 per cent zinc, 0.003 to 0.053 per cent cadmium and 4.9 to 9.9 grams per tonne silver. Assessment Report 25158
SAMPLE 1997	N Rock	Assay/analysis Copper	1.473 %	A sample (28335) from a small limonite and malachite-stained shear, located a short distance north-northeast. Assessment Report 25158
SAMPLE 1996	N Grab	Assay/analysis Copper	0.95 %	Two grab samples (28518 and 28519) of brecciated and silicified volcanics hosting malachite and chalcocite associated with quartz veinlets, carbonate, chlorite, epidote, limonite and trace sericite from the approximate occurrence area assayed 0.82 and 0.95 per cent copper, respectively. Assessment Report 24522
SAMPLE 1996	N Grab	Assay/analysis Molybdenum Copper Lead Zinc Cadmium Silver	0.024 % 1.62 % 0.97 % 8.09 % 0.100 % 20.8 g/t	A grab and a 2 metre chip sample (28520 and 28521) of brecciated and silicified volcanic hosting fine grained pyrite, galena, sphalerite, malachite, tetrahedrite(?) and smithsonite(?), located a short distance south, yielded 0.024 and 0.002 per cent molybdenum, 1.62 and 0.61 per cent copper, 0.97 and 0.19 per cent lead, 8.09 and 3.83 per cent zinc, 0.100 and 0.054 per cent cadmium with 20.8 and 7.3 grams per tonne silver, respectively. Assessment Report 24522
SAMPLE 1987	N Rock	Assay/analysis Copper Silver	3.53 % 4.3 g/t	Two rock samples (6754 and 6807) from the occurrence area yielded 3.53 and 1.06 per cent copper with 4.3 and 6.6 grams per tonne silver, respectively. Assessment Report 17118
SAMPLE 1985	N Rock	Assay/analysis Copper Silver	2.176 % 25.1 g/t	A rock sample (2066), taken several hundred metres to the south of the previous trench samples. Assessment Report 14141

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
TRENCH		Silver	5.3750 g/t	Average of four rock samples taken over 85 metres.
1985	Assay/analysis Rock	Copper	0.7105 %	Assessment Report 14141, Drawing 5b (samples 2059-2062).