MINFILE Number: 092HNE176 **Name:** RATS **Status:** Prospect

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2014 N	Assay/analysis Rock	Copper	0.57 %	Rock samples yielded an average of 0.57 per cent copper with maximum values of 2.2 per cent copper, 38 grams per tonne silver and 0.17 per cent lead Butler, S.P. (2018-06-08): Technical Report of the Castle Project in BC
TRENCH 1971 N	Assay/analysis Chip	Silver Copper	3.4000 g/t 0.1700 %	Average grade over 51.8 metres. Property File - G.E.A. von Rosen, 1971, page 8.