

| | | |
|----------------------------------|--------------------------|-------------------------|
| MINFILE Number: 092HNE186 | Name: GOLDEN LODE | Status: Prospect |
|----------------------------------|--------------------------|-------------------------|

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|---------------------------------------|--------------------------|---------------------------------|--|
| TRENCH 2017 | N Assay/analysis Chip | Copper Silver Gold | 0.626 % 24 g/t 2.69 g/t | while a chip sample (B-08), taken from the south wall of the east end of the trench over 1.2 metres Kerr, J.R. (2018-04-04): Technical Report on the Kathleen Mountain Property |
| DUMP 2011 | N Assay/analysis Grab | Copper Silver Gold | 1.32 % 41 g/t 1.857 g/t | a sample (B-05) of high-grade magnetite from a dump located near the east end of the trench Kerr, J.R. (2018-04-04): Technical Report on the Kathleen Mountain Property |
| DRILLHOLE 2000 | N Assay/analysis Drill Core | Gold Silver Copper | 6.10 g/t 23.79 g/t 0.79 % | diamond drilling on the main trench area yielded intercepts including 2.07 and 6.10 grams per tonne gold, 9.69 and 23.79 grams per tonne silver with 0.36 and 0.79 per cent copper over 3.1 and 1.38 metres, respectively, in holes GL2000-2 and GL2000-3 Kerr, J.R. (2018-04-04): Technical Report on the Kathleen Mountain Property |
| SHOWING 1979 | Assay/analysis Chip | Silver Gold | 9.3000 g/t 12.8000 g/t | Sample of magnetite-rich mineralization across 1.50 metres. Assessment Report 7988, page 6 (sample 5666). |