

MINFILE Number:	092HNE186	Name:	GOLDEN LODGE	Status:	Prospect
------------------------	-----------	--------------	--------------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2017	N	Assay/analysis Chip	Copper	0.626 %	while a chip sample (B-08), taken from the south wall of the east end of the trench over 1.2 metres Kerr, J.R. (2018-04-04): Technical Report on the Kathleen Mountain Property
			Silver	24 g/t	
			Gold	2.69 g/t	
2011	N	Assay/analysis Grab	Copper	1.32 %	a sample (B-05) of high-grade magnetite from a dump located near the east end of the trench Kerr, J.R. (2018-04-04): Technical Report on the Kathleen Mountain Property
			Silver	41 g/t	
			Gold	1.857 g/t	
2000	N	Assay/analysis Drill Core	Gold	6.10 g/t	diamond drilling on the main trench area yielded intercepts including 2.07 and 6.10 grams per tonne gold, 9.69 and 23.79 grams per tonne silver with 0.36 and 0.79 per cent copper over 3.1 and 1.38 metres, respectively, in holes GL2000-2 and GL2000-3 Kerr, J.R. (2018-04-04): Technical Report on the Kathleen Mountain Property
			Silver	23.79 g/t	
			Copper	0.79 %	
1979		Assay/analysis Chip	Silver	9.3000 g/t	Sample of magnetite-rich mineralization across 1.50 metres. Assessment Report 7988, page 6 (sample 5666).
			Gold	12.8000 g/t	