

MINFILE Number:	092HNE240	Name:	COKE	Status:	Prospect
------------------------	-----------	--------------	------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2015	N	Assay/analysis Chip	Copper	0.36 %	A chip sample from an outcrop with malachite staining over 15.5 metres. Assessment Report 35886
			Gold	0.29 g/t	
2015	N	Assay/analysis Rock	Copper	0.666 %	Four samples (J486280, M457301, M457953 and M458626) taken to the south yielded from 0.351 to 0.666 per cent copper, 1.9 to 2.9 grams per tonne silver, 0.085 to 0.862 gram per tonne gold and 0.005 to 0.103 gram per tonne palladium. Assessment Report 36184
			Silver	2.9 g/t	
			Gold	0.862 g/t	
			Palladium	0.103 g/t	
2015	N	Assay/analysis Rock	Copper	0.990 %	A sample (M457303) from the northern end of the mineralized zone Assessment Report 36184
			Silver	5.7 g/t	
			Gold	0.273 g/t	
2013	N	Assay/analysis Grab	Copper	0.652 %	Maximum values from four representative outcrop and trench samples. PR REL West Cirque Resources Ltd., Jun. 11, 2013
			Silver	52.2 g/t	
			Gold	0.233 g/t	
2010	N	Assay/analysis Grab	Gold	0.556 g/t	A grab sample (55104) from an outcrop of crystal tuff with pyrite and lesser chalcopyrite. Assessment Report 31916
			Copper	0.671 %	
2002	N	Assay/analysis Drill Core	Copper	0.19 %	Drilling yielded intercepts including 0.19 per cent copper and 0.07 gram per tonne gold over 20.0 metres (16.8 metres true thickness, 94.3 to 114.3 metres down-hole) and 0.13 per cent copper with 0.105 gram per tonne gold over 9.1 metres (6.2 metres true thickness, 80.8 to 89.9 metres down-hole) in hole 2-11. Assessment Report 26944
			Gold	0.07 g/t	
1985	N	Assay/analysis Rock	Copper	0.449 %	Two rock samples (2039 and 2040) from the occurrence area yielded 0.449 and 0.237 per cent copper, 3.1 and 2.3 grams per tonne silver with 0.105 and 0.010 gram per tonne gold, respectively. Assessment Report 14141
			Silver	3.1 g/t	
			Gold	0.105 g/t	
1975	N	Assay/analysis Drill Core	Copper	0.2300 %	Average grade over 83.2 metres (29.6-112.8 metres down-hole) in hole K-4 Property File - L. Sookochoff, 1975, page 11
1975	N	Assay/analysis Chip	Copper	0.41 %	Chip sampling of trenches is reported to have yielded 0.20 and 0.41 per cent copper over 51 and 24 metres, respectively, in trench 1 and 0.28 per cent copper with 9.9 grams per tonne silver over 24 metres in trench 4. Assessment Report 6036

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
DRILLHOLE			Copper	0.27 %	Over 18 metres (42 to 60 metres down-hole) in hole A3
1966	N	Assay/analysis Drill Core			Assessment Report 985