

<b>MINFILE Number:</b> 092HNE243	<b>Name:</b> MAN	<b>Status:</b> Prospect
----------------------------------	------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
TRENCH  2018	N  Assay/analysis Grab	Copper Gold	0.815 % 0.142 g/t	A sample (D3) from a historic trench. Assessment Report 37988
ROADCUT  2008	N  Assay/analysis Chip	Copper Gold	0.109 % 0.21 g/t	Sampling of a roadcut exposing copper mineralization yielded 0.109 per cent copper and 0.21 gram per tonne gold over 6.0 metres. Assessment Report 31709
DRILLHOLE  2008	N  Assay/analysis Drill Core	Copper Gold	0.22 % 0.61 g/t	Two diamond drillholes (858-021 and -022) on the northeastern portion of the mineralized zone yielded intercepts including 0.22 and 0.22 per cent copper with 0.61 and nil gram per tonne gold over 14.0 and 24.0 metres, respectively, while another hole (858-025), located near the centre of the mineralized zone, yielded 0.13 per cent copper over 44.0 metres. Assessment Report 31709
DRILLHOLE  2007	N  Assay/analysis Drill Core	Copper Gold	0.21 % 0.39 g/t	Drill holes 694-007, -008, -012 and -013 extended the mineralized zone 150 metres to the southwest and to a depth of approximately 200 metres. Drilling intercepts included 0.35 per cent copper and 1.41 grams per tonne gold over 22.0 metres in hole 694-008, 0.21 per cent copper and 0.39 gram per tonne gold over 92.0 metres in hole 694-012 and 0.26 per cent copper and 0.46 gram per tonne gold over 56.0 metres in hole 694-013. Assessment Report 31709
DRILLHOLE  1989	Assay/analysis Drill Core	Gold Copper	0.2700 g/t 0.2900 %	Average grade over 193.85 metres. Assessment Report 18776, page 6 (hole 321-1, 15.54 to 209.39 metres).
MAIN  1988	Assay/analysis Drill Core	Gold Copper	0.3100 g/t 0.4000 %	Average grade over 225 metres length and 10 to 30 metres width, to a depth of 230 metres. Property File - D.C. Miller, 1988, page 6.

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
DRILLHOLE		Copper	0.35 %	Diamond drilling and trenching had intersected significant copper and gold mineralization over an area of 260 by 300 metres. The bulk of the copper mineralization occurs in one prominent north-trending zone, 200 to 225 metres long and 10 to 30 metres wide, averaging 0.3 to 0.4 per cent copper and 0.31 gram per tonne gold with up to 6.8 grams per tonne gold over 3 metres in hole 80-1. Other specific drilling intercepts included 0.31 per cent copper and 0.4 gram per tonne gold over 6 metres (197.0 to 203.0 metres down-hole) and 0.23 per cent copper with 1.4 grams per tonne gold over final 3 metres (230.4 to 233.4 metres down-hole) in hole 81-1 and 0.16 per cent copper over the final 9 metres (230.0 to 239.0 metres down-hole) of hole 81-2. Assessment Report 9367, 13231 and 16985; Property File - D.C. Miller, 1988, page 6
1981	Assay/analysis Drill Core	Gold	0.31 g/t	
N				
TRENCHES		Gold	8.6 g/t	Sampling of trenches yielded significant gold values, including 8.6 grams per tonne over 5 metres and 3.57 grams per tonne over 14 metres. Assessment Report 16985 and 17077
1981	Assay/analysis Chip			
N				
TRENCHES		Copper	0.583 %	Sample 6798 Assessment Report 7584
1979	Assay/analysis Chip	Gold	1.4 g/t	
N				