

MINFILE Number: 092HNW023	Name: JULIE	Status: Prospect
----------------------------------	--------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
MAIN 2005	N Assay/analysis Chip	Copper Zinc Silver Cadmium Molybdenum	0.266 % 34.92 % 100 g/t 0.2 % 0.049 %	1.0 by 0.5 metre chip samples (5109 and 5110) yielded up to 0.049 per cent molybdenum, 0.266 per cent copper, 34.92 per cent zinc, greater than 0.200 per cent cadmium and greater than 100 grams per tonne silver Assessment Report 28410
MAIN 1989	N Assay/analysis Drill Core	Copper Lead Zinc Silver Gold	0.068 % 0.308 % 0.494 % 313.4 g/t 0.12 g/t	drilling yielded intercepts including 0.068 per cent copper, 0.308 per cent lead, 0.494 per cent zinc, 313.4 grams per tonne silver and 0.12 gram per tonne gold over 3.0 metres (41.5 to 44.5 metres down-hole) in hole 89-J3 and 0.278 per cent zinc with 16.5 grams per tonne silver over 37.0 metres in hole 89-J1 (70.5 to 107.5 metres down-hole), including 0.029 per cent molybdenum, 0.101 per cent copper, 0.099 per cent lead, 0.401 per cent zinc and 102.3 grams per tonne silver over 1.0 metre Assessment Report 19139
MAIN 1981	N Assay/analysis Drill Core	Gold	8.5700 g/t	Sample from drill hole 81-J1 across 6.1 metres. Assessment Report 19139.
MAIN 1978	N Assay/analysis Rock	Lead Zinc Silver	0.133 % 0.310 % 17.6 g/t	two rock samples (K17-2 and -3) from the Julie occurrence Assessment Report 7135
NORTHEAST 1973	N Assay/analysis Drill Core	Zinc	0.44 %	a drill hole (NC-3-73), located approximately 800 metres east- north east of the Julie occurrence, yielded 0.44 per cent zinc over 15 metres of brecciated quartz monzonite with pervasive clay-sericite and disseminated pyrite Assessment Report 7135
MAIN 1966	N 96,765 t Unclassified	Copper Zinc Silver	0.1 % 0.6 % 8.5 g/t	drilling and trenching is reported to have traced the Julie occurrence over an area of 24 metres wide, 60 metres long and 24 metre deep containing approximate 96,765 tonnes estimated to average 0.1 per cent copper, 0.6 per cent zinc and 8.5 grams per tonne silver Assessment Report 7135
MAIN 1966	N Assay/analysis Drill Core	Zinc Copper Silver	1.74 % 0.12 % 12.7 g/t	Ten of the drill holes are reported to have yielded an average of 1.74 per cent zinc, 0.12 per cent copper and 12.7 grams per tonne silver over an average of 21 metres Assessment Report 28410

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
NORTH 1954 N	Assay/analysis Grab	Silver	1984 g/t	a sample from a 5 centimetre wide vein, exposed at surface near the Stenvold workings Property File - 650178