

<b>MINFILE Number:</b> 092HSE145	<b>Name:</b> PUNCH BOWL WEST	<b>Status:</b> Showing
----------------------------------	------------------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 1988	N Assay/analysis Chip	Gold	0.300 g/t	a rock chip samples of brecciated sandstone and conglomerate containing patchy pyrite and irregular silicification Assessment Report 17824
SHEAR 1987	N Assay/analysis Chip	Silver Gold Zinc	28.0000 g/t 0.1800 g/t 0.1120 %	Chip sample taken across 3 metres of sheared sandstone. Property File - D.G. Cardinal, 1987, pages 12, 13.
VEIN 1987	N Assay/analysis Chip	Silver Gold Copper Lead Zinc	100.0000 g/t 0.1900 g/t 0.0118 % 0.1700 % 0.0600 %	Silver grade is greater than 100 grams per tonne. Chip sample taken over a width of 0.40 metre. Assessment Report 16279, page 6.
SAMPLE 1984	N Assay/analysis Grab	Gold Silver	0.300 g/t 6.0 g/t	six grab samples assayed 0.080 to 0.300 gram per tonne gold and 0.8 to 6.0 grams per tonne silver Assessment Report 14693, page 8