MINFILE Number: 092ISE012 **Name:** BERTHA - MOLLY **Status:** Past Producer

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2019 N	Assay/analysis Grab	Copper Silver	8.48 % 3.9 g/t	Three grab samples (MOL-1, -2 and -8) yielded from 1.02 to 8.48 per cent copper and 1.2 to 3.9 grams per tonne silver. Assessment Report 38305
SAMPLE 1930 N	Assay/analysis Chip	Copper	1 %	Historic sampling of the occurrence is reported to have yielded greater than 1 per cent copper over widths of 1.8 to 7.5 metres, while a drill hole (No.17) is reported to have yielded sludge samples of 0.35 and 0.50 per cent copper over 12.0 and 8.1 metres, respectively Assessment Report 14959