

MINFILE Number:	092ISE027	Name:	LUCKY MIKE	Status:	Past Producer
------------------------	-----------	--------------	------------	----------------	---------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
DRILLHOLE			Tungsten	0.17 %	Drilling on the Luck Mike occurrence yielded intercepts including 0.15 per cent tungsten over 20 metres in hole LM-2, 0.17 per cent copper, 26.4 grams per tonne silver and 0.12 per cent tungsten over 9 metres in hole LM-3 and 0.17 per cent tungsten over 23.9 metres in hole LM-4, while another drill hole (LM-7) located several hundred metres north of the previous holes yielded 0.22 per cent zinc over 42.08 metres, including 0.2 per cent copper, 0.08 per cent tungsten with 8.6 grams per tonne silver over 24.83 metres Assessment Report 35480
2014	N	Assay/analysis Drill Core			
TRENCH			Copper	3.537 %	a 1.0 metre chip sample (80964) Turner, J.A. (2012-09-17): Technical Report NI 43-101 for the Lucky Mike Copper-Tungsten Property
		Assay/analysis	Silver	82.5 g/t	
2011	N	Chip	Tungsten	0.41 %	
DRILLHOLE			Copper	0.25 %	0.25 per cent copper, 8.7 grams per tonne silver and 0.26 gram per tonne gold over 2.5 metres and 5.41 per cent copper, 160.4 grams per tonne silver and 0.60 gram per tonne gold over 0.24 metre in hole 93-7 located on a magnetic anomaly Turner, J.A. (2013-03-14): Technical Report NI 43-101 for the Lucky Mike Copper-Tungsten Property
		Assay/analysis	Silver	8.7 g/t	
1993	N	Drill Core	Gold	0.26 g/t	
DRILLHOLE			Silver	38.3900 g/t	Tungsten assay across 14.1 metres of mineralized skarn. Copper and silver assays are across 3.6 metres of mineralized skarn. Assessment Report 18583.
		Assay/analysis	Copper	0.1800 %	
1988		Drill Core	Tungsten	0.1520 %	
TOTAL		317,485 t	Silver	20.5000 g/t	Estimated geologic reserves. Assessment Report 24600, page iii.
		Indicated	Copper	0.5600 %	
1973	Y		Tungsten	0.2300 %	
TRENCH			Tungsten	0.25 %	tungsten tri-oxide over a width of 10.2 metres (Turner, J.A. (2012-09-17): Technical Report NI 43-101 for the Lucky Mike Copper-Tungsten Property
1943	N	Assay/analysis Chip			
DRILLHOLE			Tungsten	0.312 %	tungsten tri-oxide in eight holes over an average width of 7.5 metres Turner, J.A. (2012-09-17): Technical Report NI 43-101 for the Lucky Mike Copper-Tungsten Property
1943	N	Assay/analysis Drill Core			