MINFILE Number: 092ISE039 **Name:** HANK 1-4 **Status:** Showing

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
TRENCHES 1970 N	Assay/analysis Grab	Copper	3.5 %	sampling of trenches is reported to have yielded up to 3.5 per cent copper from mineralized marble and siliceous lenses and 0.4 to 1.2 per cent copper from actinolite skarn and dirty recrystalized limestone Property File – 800026
DRILLHOLE 1962 N	Assay/analysis Drill Core	Copper	0.30 %	drill hole no. 2, located on the Hank 4 claim, yielded 0.20 and 0.30 per cent copper over 4.5 and 3.0 metres, respectively Property File – 801595
TRENCH 1961 N	Assay/analysis Chip	Copper	1.65 %	sampling of a trench on the Hank 4 claim yielded 1.65 per cent copper over 0.6 metre Property File – 801606