

MINFILE Number:	092ISE039	Name:	HANK 1-4	Status:	Showing
------------------------	-----------	--------------	----------	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
TRENCHES			Copper	3.5 %	sampling of trenches is reported to have yielded up to 3.5 per cent copper from mineralized marble and siliceous lenses and 0.4 to 1.2 per cent copper from actinolite skarn and dirty recrystallized limestone Property File – 800026
1970	N	Assay/analysis Grab			
DRILLHOLE			Copper	0.30 %	drill hole no. 2, located on the Hank 4 claim, yielded 0.20 and 0.30 per cent copper over 4.5 and 3.0 metres, respectively Property File – 801595
1962	N	Assay/analysis Drill Core			
TRENCH			Copper	1.65 %	sampling of a trench on the Hank 4 claim yielded 1.65 per cent copper over 0.6 metre Property File – 801606
1961	N	Assay/analysis Chip			