MINFILE Number: 092ISE047 **Name:** MOUSE **Status:** Showing

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
43 BLOCK 2014 N	Assay/analysis Grab	Copper Silver	0.757 % 8.3 g/t	a grab sample (7630) from the fourth zone of mineralization Assessment Report 35198
SAMPLE 1968 N	Assay/analysis Grab	Silver	13.7 g/t	a sample (no. 10) of granitized diorite with disseminated pyrite. The exact location of this sample is not known. Property File - 10496
2 1965 N	Assay/analysis Grab	Copper	3.75 %	three grab samples from the second zone of mineralization yielded from 1.15 to 3.75 per cent copper Property File - 10502
1 1961 N	Assay/analysis Grab	Copper Lead Silver	0.9 % 2.60 % 66.7 g/t	grab samples from the first zone of mineralization are reported to have yielded an average of approximately 0.9 per cent copper, 0.15 to 2.60 per cent lead and 20.5 to 66.7 grams per tonne silver Property File - 10497