

<b>MINFILE Number:</b>	092ISE047	<b>Name:</b>	MOUSE	<b>Status:</b>	Showing
------------------------	-----------	--------------	-------	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
43 BLOCK			Copper	0.757 %	a grab sample (7630) from the fourth zone of mineralization Assessment Report 35198
2014	N	Assay/analysis Grab	Silver	8.3 g/t	
SAMPLE			Silver	13.7 g/t	a sample (no. 10) of granitized diorite with disseminated pyrite. The exact location of this sample is not known. Property File - 10496
1968	N	Assay/analysis Grab			
2			Copper	3.75 %	three grab samples from the second zone of mineralization yielded from 1.15 to 3.75 per cent copper Property File - 10502
1965	N	Assay/analysis Grab			
1			Copper	0.9 %	grab samples from the first zone of mineralization are reported to have yielded an average of approximately 0.9 per cent copper, 0.15 to 2.60 per cent lead and 20.5 to 66.7 grams per tonne silver Property File - 10497
			Lead	2.60 %	
1961	N	Assay/analysis Grab	Silver	66.7 g/t	