

<b>MINFILE Number:</b>	092ISE048	<b>Name:</b>	GUICHON	<b>Status:</b>	Developed Prospect
------------------------	-----------	--------------	---------	----------------	--------------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE		Assay/analysis Grab	Gold	0.43 g/t	a grab sample (7627) from a shear zone hosting quartz veinlets, located on the Camperdown crown grant Assessment Report 35198
2014	N				
DRILLHOLE		Assay/analysis Drill Core	Gold	1.50 g/t	over 1.5 metres in hole P.H.-Q-7 located on strike between the No. 1 and Fence veins Assessment Report 8074.
1980	N		Silver	6.6 g/t	
DRILLHOLE		Assay/analysis Drill Core	Gold	2.06 g/t	over 1.5 metres in hole P.H.-Q-6 which tested the fault extension to the east of the no. 2 vein Assessment Report 8074
1980	N		Silver	7.5 g/t	
DRILLHOLE		Assay/analysis Drill Core	Gold	0.96 g/t	in hole P.H.-Q-3 which tested the mineralized dike and possible related veins on the Ingersoll crown grant Assessment Report 8074
1980	N		Silver	4.1 g/t	
			Copper	0.35 %	
DRILLHOLE		Assay/analysis Drill Core	Molybdenum	0.055 %	drilling on geophysical anomalies on the Ensign and Ingersoll claims yielded 0.055 per cent molybdenite over 30 metres, including 0.099 per cent molybdenite over 6 metres in hole R-1, 0.059 per cent molybdenite over 18.9 metres in hole R-2, 0.061 per cent molybdenite over 27 metres in hole no. 4 and 2.5 grams per tonne gold, 23.1 grams per tonne silver and 0.44 per cent copper over 12 metres and 0.051 per cent molybdenite over 12 metres in hole no. 3 Property File - 810697
1966	N				
TUNNEL		Assay/analysis Chip	Gold	10.9 g/t	sampling of the no. 3, 4 and 6 tunnels yielded 10.9, 9.6 and 3.8 grams per tonne gold, 61.6, 49.6 and 27.4 grams per tonne silver with trace, 0.25 and 0.20 per cent copper over 0.40, 0.45 and 0.33 metre, respectively Property File - 810696
1965	N		Silver	61.6 g/t	
VEIN		Assay/analysis Grab	Copper	0.85 %	from the Camperdown (No. 6 or ??) vein Property File - 810696
1965	N		Silver	99.2 g/t	
			Gold	27.4 g/t	
VEIN		Assay/analysis Chip	Copper	0.50 %	over 0.3 metre from an open cut on the Ensign claim (Property File - 810696
1965	N		Gold	13.0 g/t	
			Silver	109.4 g/t	

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
NO. 2 VEIN			Gold	12.3 g/t	a drill hole (no. 2) located on the No. 2 vein yielded intercepts of 12.3 and 9.2 grams per tonne gold, 44.5 and 12.0 grams per tonne silver with 0.35 and 0.17 per cent copper over 1.5 and 0.6 metres, respectively Assessment Report 8074
1961	N	Assay/analysis	Silver	44.5 g/t	
		Drill Core	Copper	0.35 %	
NO. 2 VEIN			Gold	39.0 g/t	over 0.3 metre from an adit on the No. 2 vein Property File - 673633
1949	N	Assay/analysis	Silver	123.1 g/t	
		Chip			
VEIN			Gold	14.4 g/t	from an open cut on the No. 4 vein Property File - 673633
		Assay/analysis	Silver	88.9 g/t	
1949	N	Grab	Copper	0.15 %	
VEIN			Gold	31.1 g/t	over 0.1 metre at 46.5 metres from an adit portal on the No. 4 or 5 vein Property File - 673633
		Assay/analysis	Silver	160.7 g/t	
1949	N	Grab			
VEIN			Gold	13.0 g/t	over 0.3 metre from a pit exposing the No. 7 vein Property File - 673633
		Assay/analysis	Silver	44.5 g/t	
1949	N	Chip	Copper	0.94 %	
8			Gold	16.4 g/t	from a 3 metres long and 0.2 metre wide channel sample on the No. 8 or 9 vein Property File - 673633
		Assay/analysis	Silver	13.7 g/t	
1949	N	Chip	Copper	0.43 %	
NO. 1 VEIN			Gold	1.7 g/t	over 0.50 metre from an adit on the No. 1 vein Property File - 673633
		Assay/analysis	Silver	17.1 g/t	
1949	N	Chip	Copper	0.47 %	
DRILLHOLE			Copper	0.15 %	A pre-1947, drill hole (no. 14) located on the Ingersoll claim to test the no. 5 vein, sample over 2.53 metres of drill core sludge Assessment Report 8074
		Assay/analysis	Silver	137.0 g/t	
1947	N	Drill Core			
VEIN			Gold	20.3 g/t	a select sample (379-B) over 0.1 metre from the no. 5 vein Property File - 10508
		Assay/analysis	Copper	3 %	
1946	N	Grab			
VEIN			Gold	12.9 g/t	a representative 0.3 metre sample (378-B) from the no. 6 vein Property File - 10508
		Assay/analysis			
1946	N	Chip			
VEIN			Gold	16.8 g/t	a sample across 0.45 metres of the Fence vein from a shaft Assessment Report 8074
		Assay/analysis	Silver	10.6 g/t	
1922	N	Chip	Copper	2.93 %	

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
NO. 1 VEIN		Assay/analysis	Gold	23.9 g/t	two samples from the No. 1 vein are reported to have yielded 23.9 and 10.9 grams per tonne gold with 23.9 and 37.6 grams per tonne silver, respectively Assessment Report 8074
1922	N		Silver	37.6 g/t	
NO. 2 VEIN		Assay/analysis	Gold	14.0 g/t	sampling of the No. 2 vein from outcrop and tunnels yielded from 1.4 to 21.9 grams per tonne gold with 13.7 to 95.8 grams per tonne silver, while a 0.45 metre wide and 6.0 metre long channel sample yielded 14.0 grams per tonne gold and 69.4 grams per tonne silver Assessment Report 8074
1922	N		Silver	69.4 g/t	
		Channel			