

<b>MINFILE Number:</b> 092ISE052	<b>Name:</b> LEADVILLE	<b>Status:</b> Past Producer
----------------------------------	------------------------	------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE		Silver	58.3 g/t	Two samples (B829282 and B829283) from the Leadville adit area yielded 0.04 and 0.22 gram per tonne gold, 21.4 and 58.3 grams per tonne silver, 1.09 and 0.75 per cent lead with 0.99 and 0.89 per cent zinc, respectively. Besserer, D. (2021-05-21): NI 43-101 Technical Report for the Comstock Property, Nicola Valley, South-Central Interior of British Columbia
2020	Assay/analysis	Lead	0.75 %	
N	Rock	Zinc	0.89 %	
NORTHEAST		Copper	1.185 %	A grab sample (LD18-2) from a zone of sheared quartz vein with malachite staining in an altered rhyolite, located approximately 600 metres northeast of the shaft. Assessment Report 37588
2018	Assay/analysis	Lead	0.202 %	
N	Grab	Zinc	0.738 %	
		Silver	428 g/t	
SHAFT		Lead	0.996 %	A grab sample from the shaft area. Assessment Report 34963
2014	Assay/analysis	Zinc	0.586 %	
N	Grab	Silver	11.9 g/t	
SHAFT		Lead	1 %	A sample (05TP001) of massive barite from the east side of the Lucky Todd shaft. Assessment Report 27926
2005	Assay/analysis	Zinc	0.366 %	
N	Grab	Silver	32.5 g/t	
NORTHEAST		Copper	1 %	A sample (05WP046) from historic trenches exposing shear zone with quartz veins and copper mineralization (chalcopyrite?), located approximately 600 metres to the northeast of the shaft. Assessment Report 27926
2005	Assay/analysis	Silver	100 g/t	
N	Grab			
NORTHEAST		Copper	0.942 %	Samples from an area of trenching, located approximately 650 metres north east of the shaft. Assessment Report 12860
1984	Assay/analysis	Silver	47.9 g/t	
N	Grab			
NORTH		Copper	0.439 %	A sample taken approximately 500 metres north-northwest of the shaft. Assessment Report 12860
1984	Assay/analysis			
N	Grab			
NORTHEAST		Copper	0.80 %	Samples from an area of altered felsic volcanics, located approximately 650 metres northeast of the Lucky Todd shaft. Assessment Report 6248
1977	Assay/analysis	Zinc	0.80 %	
N	Grab	Lead	0.18 %	
		Silver	10.0 g/t	