

MINFILE Number: 092ISE054	Name: PORCUPINE	Status: Developed Prospect
----------------------------------	------------------------	-----------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SHAFT 2007 N	Assay/analysis Chip	Copper Silver	1.93 % 8.0 g/t	Composite chip samples (E111-1 and E111-2) of auto-breccia exposed on the north and south walls of the shaft yielded 1.93 and 0.92 per cent copper with 8.0 and 2.4 grams per tonne silver over 1.2 and 1.0 metres, respectively. Assessment Report 31213
DRILLHOLE 1969 N	Assay/analysis Drill Core	Copper	2.21 %	Drilling was completed with in approximately 200 metres the shaft and yielded from 6.35 per cent copper over 3.6 metres in hole 4 to 0.32 per cent copper over 28.2 metres in hole 12, while the average of 12 drill holes yielded a grade of 2.21 per cent copper across 28.5 metres. Property File – 10525 and 800307
PORCUPINE 1969 Y	453,550 t Inferred	Copper	1.9000 %	Possible. Northern Miner - December 4, 1969.
SHAFT 1969 N	Assay/analysis Chip	Copper	1.79 %	Chip and channel sampling of the shaft yielded an average of 1.79 per cent copper over 12.0 metres. Property File – 10527
PORCUPINE 1967 Y	125,179 t Indicated	Copper	2.0000 %	Drill indicated. Northern Miner - February 2, 1967.