

MINFILE Number: 092ISE132	Name: PEACOCK	Status: Showing
----------------------------------	----------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
FLOAT		Copper	6.78 %	three float samples (P4, P5 and P7) from the Peacock occurrence area yielded from 2.71 to 6.78 per cent copper with 34 to 83 grams per tonne silver Assessment Report 35529
2015	Assay/analysis Grab	Silver	83 g/t	
SAMPLE		Silver	17.5 g/t	two samples (29 and 30) yielded greater than 1 per cent copper each with 9.3 and 17.5 grams per tonne silver and 0.377 and 0.633 gram per tonne gold, respectively. These samples were later re-sampled and yielded 1.33 and 2.31 per cent copper, respectively Assessment Report 33375 and 35529
2012	Assay/analysis Grab	Gold	0.633 g/t	
		Copper	2.31 %	
SAMPLE		Gold	4.98 g/t	a sample (no. 1) from the Clapperton Creek (Peacock) occurrence area Assessment Report 35529
2010	Assay/analysis Grab	Silver	287 g/t	
		Copper	21.4 %	
SAMPLE		Gold	1.03 g/t	sample 53063 Assessment Report 19933
1992	Assay/analysis Grab	Silver	35.4 g/t	
		Copper	1.69 %	
TRENCH		Gold	0.34 g/t	In the 1940s or early 1950s, sampling of a trench is reported to have yielded 0.34 gram per tonne gold, 39.3 grams per tonne silver and 3.1 per cent copper over 13.5 metres Property File - 811079
1950	Assay/analysis Chip	Silver	39.3 g/t	
		Copper	3.1 %	