**MINFILE Number:** 092ISE132 **Name:** PEACOCK **Status:** Showing

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|---|---|---|---|---|
| FLOAT<br>2015 N | Assay/analysis<br>Grab | Copper<br>Silver | 6.78 %<br>83 g/t | three float samples (P4, P5 and P7) from the Peacock occurrence area yielded from 2.71 to 6.78 per cent copper with 34 to 83 grams per tonne silver<br>Assessment Report 35529 |
| SAMPLE<br>2012 N | Assay/analysis<br>Grab | Silver<br>Gold<br>Copper | 17.5 g/t<br>0.633 g/t<br>2.31 % | two samples (29 and 30) yielded greater than 1 per cent copper each with 9.3 and 17.5 grams per tonne silver and 0.377 and 0.633 gram per tonne gold, respectively. These samples were later re-sampled and yielded 1.33 and 2.31 per cent copper, respectively<br>Assessment Report 33375 and 35529 |
| SAMPLE<br>2010 N | Assay/analysis<br>Grab | Gold<br>Silver<br>Copper | 4.98 g/t<br>287 g/t<br>21.4 % | a sample (no. 1) from the Clapperton Creek (Peacock) occurrence area<br>Assessment Report 35529 |
| SAMPLE<br>1992 N | Assay/analysis<br>Grab | Gold<br>Silver<br>Copper | 1.03 g/t<br>35.4 g/t<br>1.69 % | sample 53063<br>Assessment Report 19933 |
| TRENCH<br>1950 N | Assay/analysis<br>Chip | Gold<br>Silver<br>Copper | 0.34 g/t<br>39.3 g/t<br>3.1 % | In the 1940s or early 1950s, sampling of a trench is reported to have yielded 0.34 gram per tonne gold, 39.3 grams per tonne silver and 3.1 per cent copper over 13.5 metres<br>Property File - 811079 |