

<b>MINFILE Number:</b>	092ISE196	<b>Name:</b>	PLUG	<b>Status:</b>	Prospect
------------------------	-----------	--------------	------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
1997	N	Assay/analysis Drill Core	Gold	1.30 g/t	Percussion drilling (PDH-02) tested trench-02 and returned an average of 1.30 grams per tonne gold and 17.2 grams per tonne silver over a length of 9.91 metres. Assessment Report 25405
			Silver	17.2 g/t	
1997	N	Assay/analysis Chip	Gold	4.35 g/t	Sampling trench-02 yielded an average of 4.35 grams per tonne gold and 52.2 grams per tonne silver over a strike length of 11.98 metres and a width of 1.33 metres; including 20.78 grams per tonne gold and 113.0 grams per tonne silver over a width of 0.56 metre. Assessment Report 25405
			Silver	52.2 g/t	
1995	N	Assay/analysis Rock	Gold	2.62 g/t	Five rock samples yielded from 0.060 to 2.620 grams per tonne gold and 1.8 to 114.5 grams per tonne silver. Assessment Report 24862
			Silver	114.5 g/t	
1988	N	Assay/analysis Grab	Gold	7.5 g/t	A grab sample (88-23) of carbonate altered rock from a historic trench. Assessment Report 18048
			Silver	67.5 g/t	