

MINFILE Number:		092ISW070	Name:	LL	Status:	Showing
Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments	
SAMPLE		Assay/analysis	Copper	0.402 %	two samples (322623 and 322624) yielded 0.402 and 3.750 per cent copper with 2.6 and 28 grams per tonne silver over 6 and 0.5 metres, respectively Assessment Report 30779	
2008	N	Chip	Silver	2.6 g/t		
SAMPLE		Assay/analysis	Copper	0.08 %	a chip sample (0901) of wall rock from the northwest side of the vein yielded 0.49 per cent copper and 3.4 grams per tonne silver over 0.3 metre and a chip sample (0903) of wall rock from the southeast side of the vein yielded 0.08 per cent copper, 3.4 grams per tonne silver and 2.2 grams per tonne gold over 0.3 metre Property File Document 11026	
1976	N	Chip	Silver	3.4 g/t		
			Gold	2.2 g/t		
VEIN		Assay/analysis	Copper	23.40 %	a chip sample (0902) of decayed vein material Property File Document 11026	
1976	N	Chip	Silver	103.3 g/t		
SAMPLE		Assay/analysis	Copper	42.36 %	a sample (0679) from a 15-centimetre wide lenses of green gossan interlaced with bornite in a diorite Property File Document 11028	
1975	N	Grab	Gold	0.4 g/t		
SAMPLE		Assay/analysis	Copper	0.60 %	a grab sample (0680) of the diorite host Property File Document 11028	
1975	N	Grab				