

MINFILE Number: 092ISW070	Name: LL	Status: Showing
----------------------------------	-----------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2008	N Assay/analysis Chip	Copper Silver	0.402 % 2.6 g/t	two samples (322623 and 322624) yielded 0.402 and 3.750 per cent copper with 2.6 and 28 grams per tonne silver over 6 and 0.5 metres, respectively Assessment Report 30779
SAMPLE 1976	N Assay/analysis Chip	Copper Silver Gold	0.08 % 3.4 g/t 2.2 g/t	a chip sample (0901) of wall rock from the northwest side of the vein yielded 0.49 per cent copper and 3.4 grams per tonne silver over 0.3 metre and a chip sample (0903) of wall rock from the southeast side of the vein yielded 0.08 per cent copper, 3.4 grams per tonne silver and 2.2 grams per tonne gold over 0.3 metre Property File Document 11026
VEIN 1976	N Assay/analysis Chip	Copper Silver	23.40 % 103.3 g/t	a chip sample (0902) of decayed vein material Property File Document 11026
SAMPLE 1975	N Assay/analysis Grab	Copper Gold	42.36 % 0.4 g/t	a sample (0679) from a 15-centimetre wide lende of green gossan interlaced with bornite in a diorite Property File Document 11028
SAMPLE 1975	N Assay/analysis Grab	Copper	0.60 %	a grab sample (0680) of the diorite host Property File Document 11028