

MINFILE Number: 092JNE054	Name: GOLD KING	Status: Prospect
----------------------------------	------------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
CREEK		Lead	0.482 %	A float sample (GKLS-FLO) form the Creek zone Butler, S. (2008-01-11): Summary Report on the Gold King Property
	Assay/analysis	Zinc	1 %	
2005	Grab	Silver	100 g/t	
		Gold	13.52 g/t	
SAMPLE		Gold	1.19 g/t	a rock sample (GKLS-1) taken from a mineralized zone located near a helicopter pad, south west of the Creek zone Butler, S. (2008-01-11): Summary Report on the Gold King Property
	Assay/analysis	Silver	35.1 g/t	
2005	Rock	Lead	0.224 %	
		Zinc	1 %	
SKARN		Lead	0.503 %	samples (GKLS-5 to -7) from the Gold King zone Butler, S. (2008-01-11): Summary Report on the Gold King Property
	Assay/analysis	Zinc	1 %	
2005	Rock	Silver	100 g/t	
CREEK		Gold	1.54 g/t	a sample from a newly discovered skarn zone in the Gold King occurrence area, referred to as the Creek zone Butler, S. (2008-01-11): Summary Report on the Gold King Property
	Assay/analysis	Silver	132 g/t	
2004	Grab	Zinc	12.05 %	
SKARN		Gold	0.42 g/t	grab chip sample (GK-2) from a mineralized skarn zone Butler, S. (2008-01-11): Summary Report on the Gold King Property
	Assay/analysis	Silver	37.2 g/t	
2004	Chip	Lead	0.130 %	
		Zinc	0.471 %	
DUMP		Gold	12.1 g/t	a rock sample from the 'Camp Adit' dump Butler, S. (2008-01-11): Summary Report on the Gold King Property
	Assay/analysis	Silver	56.8 g/t	
2004	Grab	Lead	0.55 %	
		Zinc	0.393 %	
VEIN		Copper	0.02 %	Sample 14212, from a 5 to 7 centimetre wide quartz vein Assessment Report 21274
	Assay/analysis	Lead	3.23 %	
1991	Grab	Zinc	0.82 %	
		Gold	4.8 g/t	
		Silver	78.3 g/t	
SAMPLE		Gold	1.0 g/t	across 1.25 metres Property File - J.A. Mitchell [1969-10-16]: Report on the D Group of Claims
	Assay/analysis	Silver	51.3 g/t	
1969	Channel	Copper	0.10 %	
		Lead	0.37 %	
		Zinc	2.40 %	
SHAFT		Gold	19.2 g/t	a grab sample, taken from an 8-metre deep shaft Minister of Mines Annual Report 1930
	Assay/analysis	Silver	308.6 g/t	
1930	Grab	Lead	0.8 %	
		Zinc	6.8 %	