

MINFILE N	umber:	092JNE079	Name: BRI	ETT	Status: Past Producer
Ore Zor Year/Report		Tonnage/ Category	Commodity	Grade	Reference/ Comments
DUMP 2005	N	Assay/analysis Grab	Gold	1.15 g/t	Assessment Report 28240
NO. 3 1983	Ν	Assay/analysis Chip	Gold	0.82 g/t	A 10 metre sample of footwall material from the No.3 adit Assessment Report 11749
UNDERGRO WORKINGS 1962	UND N	Assay/analysis Channel	Silver Gold	65.1400 g/t 293.0000 g/t	From a 2.4-metre channel sample. Minister of Mines Annual Report 1962, page 27.
TUNNEL 1947	Ν	Assay/analysis Chip	Gold	7.2 g/t	Sampling of the Mac tunnel is reported to have yielded a weighted average of 7.2 grams per tonne gold across 1.8 metres and for a length of 15 metres. Assessment Report 11749
UNDERGRO WORKINGS 1934	UND N	Assay/analysis Chip	Gold	26.7 g/t	Assay plans from the No.2 and 3 levels are reported to yield values up to 26.7 grams per tonne gold over 2.58 metres. Assessment Report 11749
NO. 3 1933	N	Assay/analysis Chip	Gold	8.5 g/t	Sampling of the No.3 drift, in 1933, is reported to have yielded 8.5 grams per tonne gold over and average width 1.5 metres, from 112 samples Assessment Report 11749
NO. 2 1910	N	Assay/analysis Rock	Gold	166.9 g/t	Sample from the No.2 drift is reported to have assayed 166.9 grams per tonne gold over 35 centimetres Assessment Report 11749