

<b>MINFILE Number:</b> 092JNE079	<b>Name:</b> BRETT	<b>Status:</b> Past Producer
----------------------------------	--------------------	------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
DUMP		Gold	1.15 g/t	Assessment Report 28240
2005	N	Assay/analysis Grab		
NO. 3		Gold	0.82 g/t	A 10 metre sample of footwall material from the No.3 adit
1983	N	Assay/analysis Chip		Assessment Report 11749
UNDERGROUND WORKINGS		Silver	65.1400 g/t	From a 2.4-metre channel sample.
1962	N	Assay/analysis Channel	Gold 293.0000 g/t	Minister of Mines Annual Report 1962, page 27.
TUNNEL		Gold	7.2 g/t	Sampling of the Mac tunnel is reported to have yielded a weighted average of 7.2 grams per tonne gold across 1.8 metres and for a length of 15 metres.
1947	N	Assay/analysis Chip		Assessment Report 11749
UNDERGROUND WORKINGS		Gold	26.7 g/t	Assay plans from the No.2 and 3 levels are reported to yield values up to 26.7 grams per tonne gold over 2.58 metres.
1934	N	Assay/analysis Chip		Assessment Report 11749
NO. 3		Gold	8.5 g/t	Sampling of the No.3 drift, in 1933, is reported to have yielded 8.5 grams per tonne gold over and average width 1.5 metres, from 112 samples
1933	N	Assay/analysis Chip		Assessment Report 11749
NO. 2		Gold	166.9 g/t	Sample from the No.2 drift is reported to have assayed 166.9 grams per tonne gold over 35 centimetres
1910	N	Assay/analysis Rock		Assessment Report 11749