

|                                  |                       |                        |
|----------------------------------|-----------------------|------------------------|
| <b>MINFILE Number:</b> 092JW 042 | <b>Name:</b> ENGINEER | <b>Status:</b> Showing |
|----------------------------------|-----------------------|------------------------|

| Ore Zone/<br>Year/Report On | Tonnage/<br>Category   | Commodity                | Grade                          | Reference/<br>Comments  |
|-----------------------------|------------------------|--------------------------|--------------------------------|---|
| SAMPLE<br>1994      N       | Assay/analysis<br>Chip | Copper                   | 0.1000 %                       | Sample Eng94-RC23 across 3.5 metres of quartz<br>feldspar porphyry.<br>Assessment Report 23623.   |
| SAMPLE<br>1988      N       | Assay/analysis<br>Grab | Gold<br>Silver<br>Copper | 0.15 g/t<br>5.6 g/t<br>0.769 % | two samples, H-Pass-1 and 2<br>Property File - Chemex Labs Ltd. [1988-10-13];<br>Certificate of Analysis - A8824969 - Chevron Canada<br>Resources Ltd. - Hurley |