

|                        |          |              |                    |                |          |
|------------------------|----------|--------------|--------------------|----------------|----------|
| <b>MINFILE Number:</b> | 092K 036 | <b>Name:</b> | WHITE PINE (L.234) | <b>Status:</b> | Prospect |
|------------------------|----------|--------------|--------------------|----------------|----------|

| Ore Zone/<br>Year/Report On |   | Tonnage/<br>Category         | Commodity  | Grade      | Reference/<br>Comments   |
|-----------------------------|---|------------------------------|------------|------------|--|
| 1987                        | N | Assay/analysis<br>Drill Core | Silver     | 3.6000 g/t | The best gold, silver and copper values obtained from intersections in drillhole ET-87-10 between 33.5 and 35.55 metres.<br>Assessment Report 17274. |
|                             |   |                              | Gold       | 0.8100 g/t |  |
|                             |   |                              | Copper     | 0.3000 %   |  |
| 1987                        | N | Assay/analysis<br>Channel    | Silver     | 5.4000 g/t | Channel across 1 metre. Also contained 12.2 per cent iron.<br>Assessment Report 17274.   |
|                             |   |                              | Gold       | 2.3100 g/t |  |
|                             |   |                              | Molybdenum | 0.0589 %   |  |
| 1934                        | N | Assay/analysis<br>Rock       | Gold       | 37.708 g/t | Select samples from Shaft No. 2<br>Minister of Mines Annual Report 1934, page F10  |
|                             |   |                              |            |            |  |