

MINFILE Number:	092K 043	Name:	IRON MIKE	Status:	Past Producer
------------------------	----------	--------------	-----------	----------------	---------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
IRON MIKE			Iron	56.71 %	Three samples (#8 through #10) from the main Iron Mike pit yielded from 30.00 to 56.71 per cent iron. Assessment Report 39307
2020	N	Assay/analysis Grab			
PITS			Iron	50 %	Three grab samples (E5125474 through E512547) of massive magnetite skarn from the Iron Steve, Iron Ross and Iron Mike zones each yielded greater than 50 per cent iron, respectively, while the sample (E5125474) from the Iron Steve zone also yielded 0.112 gram per tonne gold. Assessment Report 35055
2014	N	Assay/analysis Grab			
IRON MIKE		955,266 t Combined	Iron	43.5000 %	Proven (688,281 tonnes) and indicated (266,985 tonnes) reserves, some (168,736 tonnes) of which were mined in 1966 and 1969. Property File - H.L. Hill, May 15, 1965.
1964	Y				