

|                                 |                                 |                              |
|---------------------------------|---------------------------------|------------------------------|
| <b>MINFILE Number:</b> 092L 034 | <b>Name:</b> IRON CROWN (L.126) | <b>Status:</b> Past Producer |
|---------------------------------|---------------------------------|------------------------------|

| Ore Zone/<br>Year/Report On | Tonnage/<br>Category   | Commodity      | Grade             | Reference/<br>Comments   |
|-----------------------------|------------------------|----------------|-------------------|--|
| DUMP<br>2014 N              | Assay/analysis<br>Grab | Copper<br>Iron | 0.460 %<br>25.3 % | three tailings/dump samples yielded from 0.223 to 0.460 per cent copper, 2.4 to 4.2 grams per tonne silver and 16.9 to 25.3 per cent iron<br>Assessment Report 35179 |
| DUMP<br>2011 N              | Assay/analysis<br>Grab | Iron<br>Copper | 25.3 %<br>0.460 % | Assessment Report 33783  |
| DUMP<br>2010 N              | Assay/analysis<br>Grab | Magnetite      | 7 %               | Assessment Report 32150  |