

<b>MINFILE Number:</b> 092L 034	<b>Name:</b> IRON CROWN (L.126)	<b>Status:</b> Past Producer
---------------------------------	---------------------------------	------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
DUMP 2014 N	Assay/analysis Grab	Copper Iron	0.460 % 25.3 %	three tailings/dump samples yielded from 0.223 to 0.460 per cent copper, 2.4 to 4.2 grams per tonne silver and 16.9 to 25.3 per cent iron Assessment Report 35179
DUMP 2011 N	Assay/analysis Grab	Iron Copper	25.3 % 0.460 %	Assessment Report 33783
DUMP 2010 N	Assay/analysis Grab	Magnetite	7 %	Assessment Report 32150