

MINFILE Inventory Detail Report BC Geological Survey

Ministry of Energy, Mines and Petroleum Resources

MINFILE	Number:	092L 044	Name: ME	ERRY WIDOW 5 (L.15	Status: Past Producer
Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
KNOB 2020	N	Assay/analysis Channel	Gold Silver Copper	9.77 g/t 28.4 g/t 2.35 %	A channel sample of the Copper Knob occurrence yielded 9.77 grams per tonne gold, 28.4 grams per tonne silver and 2.35 per cent copper over 10.5 metres of semi-massive pyrite-chalcopyrite mineralization. Assessment Report 39420
SOUTH 2020	N	Assay/analysis Grab	Gold Silver Copper Cobalt	6.1 g/t 11.5 g/t 0.116 % 0.088 %	A grab sample of gossanous material, located approximately 30 metres south of the Merry Widow open-pit and referred to as the South Pit zone. Assessment Report 39420
KNOB 2019	N	Assay/analysis Rock	Gold Silver Copper Cobalt Iron Zinc	24.8 g/t 518.0 g/t 17.10 % 0.147 % 29.10 % 0.349 %	Four rock samples (Y993765 through Y993768) containing semi-massive chalcopyrite from the Copper Knob occurrence, located near the northern edge of the Merry Widow pit yielded from 13.9 to 24.8 grams per tonne gold, 74.1 to 218.0 grams per tonne silver, 7.22 to 17.10 per cent copper, 0.039 to 0.147 per cent cobalt, 10.65 to 29.10 per cent iron and 0.102 to 0.349 per cent zinc. Assessment Report 38855
MAIN 2019	N	Assay/analysis Rock	Gold Silver Copper Cobalt Iron	24.8 g/t 78.7 g/t 5.77 % 0.469 % 50 %	Seven rock samples (Y993751 through Y993756) from the Merry Widow pit yielded from 1.1 to 24.8 grams per tonne gold, 1.1 to 78.7 grams per tonne silver, 0.12 to 5.77 per cent copper, 0.006 to 0.469 per cent cobalt and 19.95 to greater than 50 per cent iron. Assessment Report 38855
MAIN 2008	Y	960 kt Combined	Gold Silver Copper Cobalt Iron	2.03 g/t 5.64 g/t 0.34 % 0.013 % 16.1 %	Measured plus indicated using a 0.50 gram per tonne gold cut-off grade. Giroux, G.H. (2008-11-30): Technical Report on the Copper-Gold Resource for the Merry Widow Property
MAIN 2008	Y	120 kt Inferred	Gold Silver Copper Cobalt Iron	0.19 g/t 2.77 g/t 0.13 % 0.008 % 16.2 %	Using a 0.50-gram per tonne gold cut-off grade. Giroux, G.H. (2008-11-30): Technical Report on the Copper-Gold Resource for the Merry Widow Property

Sunday, November 16, 2025 MINFILE Number: 092L 044 Page 1 of 1