

<b>MINFILE Number:</b>	092L 044	<b>Name:</b>	MERRY WIDOW 5 (L.1533)	<b>Status:</b>	Past Producer
------------------------	----------	--------------	------------------------	----------------	---------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2020	N	Assay/analysis Channel	Gold	9.77 g/t	A channel sample of the Copper Knob occurrence yielded 9.77 grams per tonne gold, 28.4 grams per tonne silver and 2.35 per cent copper over 10.5 metres of semi-massive pyrite-chalcopyrite mineralization. Assessment Report 39420
			Silver	28.4 g/t	
			Copper	2.35 %	
2020	N	Assay/analysis Grab	Gold	6.1 g/t	A grab sample of gossanous material, located approximately 30 metres south of the Merry Widow open-pit and referred to as the South Pit zone. Assessment Report 39420
			Silver	11.5 g/t	
			Copper	0.116 %	
			Cobalt	0.088 %	
2019	N	Assay/analysis Rock	Gold	24.8 g/t	Four rock samples (Y993765 through Y993768) containing semi-massive chalcopyrite from the Copper Knob occurrence, located near the northern edge of the Merry Widow pit yielded from 13.9 to 24.8 grams per tonne gold, 74.1 to 218.0 grams per tonne silver, 7.22 to 17.10 per cent copper, 0.039 to 0.147 per cent cobalt, 10.65 to 29.10 per cent iron and 0.102 to 0.349 per cent zinc. Assessment Report 38855
			Silver	518.0 g/t	
			Copper	17.10 %	
			Cobalt	0.147 %	
			Iron	29.10 %	
2019	N	Assay/analysis Rock	Zinc	0.349 %	Seven rock samples (Y993751 through Y993756) from the Merry Widow pit yielded from 1.1 to 24.8 grams per tonne gold, 1.1 to 78.7 grams per tonne silver, 0.12 to 5.77 per cent copper, 0.006 to 0.469 per cent cobalt and 19.95 to greater than 50 per cent iron. Assessment Report 38855
			Gold	24.8 g/t	
			Silver	78.7 g/t	
			Copper	5.77 %	
			Cobalt	0.469 %	
2008	Y	960 Combined kt	Iron	50 %	Measured plus indicated using a 0.50 gram per tonne gold cut-off grade. Giroux, G.H. (2008-11-30): Technical Report on the Copper-Gold Resource for the Merry Widow Property
			Gold	2.03 g/t	
			Silver	5.64 g/t	
			Copper	0.34 %	
			Cobalt	0.013 %	
2008	Y	120 Inferred kt	Iron	16.1 %	Using a 0.50-gram per tonne gold cut-off grade. Giroux, G.H. (2008-11-30): Technical Report on the Copper-Gold Resource for the Merry Widow Property
			Gold	0.19 g/t	
			Silver	2.77 g/t	
			Copper	0.13 %	
			Cobalt	0.008 %	
2008	Y		Iron	16.2 %	