

|                                 |                          |                        |
|---------------------------------|--------------------------|------------------------|
| <b>MINFILE Number:</b> 092L 077 | <b>Name:</b> NORTH SHORE | <b>Status:</b> Showing |
|---------------------------------|--------------------------|------------------------|

| Ore Zone/<br>Year/Report On | Tonnage/<br>Category        | Commodity                        | Grade  | Reference/<br>Comments  |
|-----------------------------|-----------------------------|----------------------------------|--|---|
| NORTH<br>1991               | N<br>Assay/analysis<br>Rock | Copper                           | 0.074 %  | two samples (38539 and 38540) of mineralized andesite from the northern (Witti 3) zone<br>Assessment Report 21607 |
| NORTH<br>1991               | N<br>Assay/analysis<br>Rock | Copper<br>Gold                   | 0.074 %<br>0.48 g/t                              | two samples (38539 and 38540) of andesite from the Witt 3 zone<br>Assessment Report 21607                         |
| SKARN<br>1988               | N<br>Assay/analysis<br>Rock | Copper<br>Zinc<br>Silver         | 9.39 %<br>10.0 %<br>150.4 g/t                    | sample NLR88-054 from trench 9 on the eastern end of the Lake zone<br>Assessment Report 18502                     |
| VEIN<br>1968                | N<br>Assay/analysis<br>Chip | Zinc<br>Lead<br>Copper<br>Silver | 6.46 %<br>3.26 %<br>0.07 %<br>186.5 g/t          | a 0.5 metre chip sample over the easternmost exposure of the vein<br>Assessment Report 1610                       |
| VEIN<br>1968                | N<br>Assay/analysis<br>Rock | Zinc<br>Lead<br>Copper<br>Silver | 9.18 %<br>53.24 %<br>0.04 %<br>4457.8 g/t        | sample from the westernmost exposure of the vein<br>Assessment Report 1610  |
| SKARN<br>1968               | N<br>Assay/analysis<br>Chip | Silver<br>Copper<br>Lead<br>Zinc | 186.5000 g/t<br>0.0700 %<br>3.2600 %<br>6.4100 % | Chip sample across 0.46 metres. Trace amounts of gold reported.<br>Assessment Report 1610.                        |
| SKARN<br>1968               | N<br>Assay/analysis<br>Chip | Copper<br>Silver                 | 1.63 %<br>12.3 g/t                               | a 1.8 metre chip sample of skarn<br>Assessment Report 1610  |