

MINFILE Number:	092L 127	Name:	HILLER 4-5	Status:	Developed Prospect
------------------------	----------	--------------	------------	----------------	--------------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
DRILLHOLE			Iron	44.43 %	Over 27.0 metres in hole H-26.
1966	N	Assay/analysis Drill Core			Property File - R.N. Saukko (1967-03-15): Report on Hiller-Churchill Properties 1966
DRILLHOLE			Iron	42.16 %	Over 84.0 metres in hole H-29.
1966	N	Assay/analysis Drill Core			Property File - R.N. Saukko (1967-03-15): Report on Hiller-Churchill Properties 1966
DRILLHOLE			Iron	43.17 %	Over 36.0 metres in hole H-31.
1966	N	Assay/analysis Drill Core			Property File - R.N. Saukko (1967-03-15): Report on Hiller-Churchill Properties 1966
DRILLHOLE			Iron	51.87 %	Over 16.5 metres in hole H-35.
1966	N	Assay/analysis Drill Core			Property File - R.N. Saukko (1967-03-15): Report on Hiller-Churchill Properties 1966
DRILLHOLE			Iron	45.44 %	Over 27.0 metres in hole H-37.
1966	N	Assay/analysis Drill Core			Property File - R.N. Saukko (1967-03-15): Report on Hiller-Churchill Properties 1966
DRILLHOLE			Iron	43.97 %	Over 75.0 metres in hole H-38.
1966	N	Assay/analysis Drill Core			Property File - R.N. Saukko (1967-03-15): Report on Hiller-Churchill Properties 1966
DRILLHOLE			Iron	44.41 %	Over 48.0 metres in hole H-41.
1966	N	Assay/analysis Drill Core			Property File - R.N. Saukko (1967-03-15): Report on Hiller-Churchill Properties 1966
DRILLHOLE			Iron	41.28 %	Over 54.0 metres in hole H-42.
1966	N	Assay/analysis Drill Core			Property File - R.N. Saukko (1967-03-15): Report on Hiller-Churchill Properties 1966
DRILLHOLE			Iron	45.99 %	Over 30.0 metres in hole H-44.
1966	N	Assay/analysis Drill Core			Property File - R.N. Saukko (1967-03-15): Report on Hiller-Churchill Properties 1966
HILLER 4		3,338 kt	Iron	35.9000 %	Drill indicated reserves from the 3000 to 3400 levels.
1966	Y	Indicated			Property File - R.N. Saukko (1967-03-15): Report on Hiller-Churchill Properties 1966

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
DRILLHOLE			Iron	41.28 %	Iron over 54.0 metres in hole H-42.
1966	N	Assay/analysis Drill Core			Property File - R.N. Saukko (1967-03-15): Report on Hiller-Churchill Properties 1966
DRILLHOLE			Iron	54.44 %	Over 53.4 metres in hole H-24.
1965	N	Assay/analysis Drill Core			Property File - R.N. Saukko [1966-02-10]: Report on Hiller-Churchill Deposit 1965
DRILLHOLE			Iron	54.25 %	Over 24.0 metres in hole H-17.
1965	N	Assay/analysis Drill Core			(Property File - R.N. Saukko [1966-02-10]: Report on Hiller-Churchill Deposit 1965
DRILLHOLE			Iron	37.7 %	Over 78.0 metres in hole H-18 which also contained another section grading 43.54 per cent iron over 33.0 metres.
1965	N	Assay/analysis Drill Core			Property File - R.N. Saukko [1966-02-10]: Report on Hiller-Churchill Deposit 1965
DRILLHOLE			Iron	36.42 %	Over 42.0 metres in hole H-19.
1965	N	Assay/analysis Drill Core			Property File - R.N. Saukko [1966-02-10]: Report on Hiller-Churchill Deposit 1965
DRILLHOLE			Iron	44.00 %	Over 42.0 metres in hole H-20.
1965	N	Assay/analysis Drill Core			Property File - R.N. Saukko [1966-02-10]: Report on Hiller-Churchill Deposit 1965
DRILLHOLE			Iron	48.23 %	Over 21.0 metres in hole H-21.
1965	N	Assay/analysis Drill Core			Property File - R.N. Saukko [1966-02-10]: Report on Hiller-Churchill Deposit 1965
DRILLHOLE			Iron	50.88 %	Over 12.0 metres in hole H-22.
1965	N	Assay/analysis Drill Core			Property File - R.N. Saukko [1966-02-10]: Report on Hiller-Churchill Deposit 1965
DRILLHOLE			Iron	42.19 %	Over 38.1 metres in hole H-23.
1965	N	Assay/analysis Drill Core			Property File - R.N. Saukko [1966-02-10]: Report on Hiller-Churchill Deposit 1965