

|                                 |                       |                        |
|---------------------------------|-----------------------|------------------------|
| <b>MINFILE Number:</b> 092L 133 | <b>Name:</b> MARTHA 4 | <b>Status:</b> Showing |
|---------------------------------|-----------------------|------------------------|

| Ore Zone/<br>Year/Report On | Tonnage/<br>Category   | Commodity | Grade    | Reference/<br>Comments   |
|-----------------------------|------------------------|-----------|----------|--|
| 3                           |                        | Copper    | 0.208 %  | A rock chip sample (S-17-12) of the mineralized gossanous zone.<br>Assessment Report 36824   |
|                             | Assay/analysis         | Zinc      | 0.502 %  |  |
| 2017                        | Rock                   | Silver    | 11.8 g/t |  |
| FLOAT                       |                        | Iron      | 24.36 %  | A float boulder sample (S-17-30) from the Storey zone.<br>Assessment Report 36824  |
|                             | Assay/analysis         | Copper    | 4.24 %   |  |
| 2017                        | Grab                   | Gold      | 0.63 g/t |  |
| SOUTHEAST                   |                        | Copper    | 0.22 %   | An outcrop sample from the fifth zone.<br>Assessment Report 36824  |
|                             | Assay/analysis         | Silver    | 4.8 g/t  |  |
| 2017                        | Rock                   | Iron      | 24.36 %  |  |
| STORIE                      |                        | Iron      | 31.11 %  | Five chip samples (S-17-24 through -28) yielded from 12.31 to 31.11 per cent iron from the Storey zone.<br>Assessment Report 36824 |
| 2017                        | Assay/analysis<br>Chip |           |          |  |
| SAMPLE                      |                        | Copper    | 0.259 %  | In 1989, a sample (SZ-1) assayed 0.101 per cent cadmium, 0.259 per cent copper and 14.9 per cent zinc.<br>Assessment Report 20092  |
|                             | Assay/analysis         | Cadmium   | 0.101 %  |  |
| 1989                        | Grab                   | Zinc      | 14.9 %   |  |
| SAMPLE                      |                        | Copper    | 0.49 %   | In 1988, a sample assayed 0.49 per cent copper and 0.31 per cent zinc over 0.6 metre.<br>Assessment Report 18704                   |
|                             | Assay/analysis         | Zinc      | 0.31 %   |  |
| 1988                        | Grab                   |           |          |  |